




# PROBLEM SUMMARY

Sample Rating Trend




Machine Id  
**728022-1149**

Component  
**Diesel Engine**

Fluid  
**CHEVRON DELO 400 XLE 15W40 (--- GAL)**

## COMPONENT CONDITION SUMMARY

### ▲ Ferrous Alloys



## RECOMMENDATION

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

## PROBLEMATIC TEST RESULTS

Sample Status				ABNORMAL	NORMAL	NORMAL
Iron	ppm	ASTM D5185m	>80	▲ 103	79	55

Customer Id: GFL624  
Sample No.: GFL0096235  
Lab Number: 06006081  
Test Package: FLEET



To manage this report scan the QR code

To discuss the diagnosis or test data:  
Don Baldrige +1  
[don.b505@comcast.net](mailto:don.b505@comcast.net)

To change component or sample information:  
Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Fluid	---	---	?	Oil and filter change at the time of sampling has been noted.
Change Filter	---	---	?	Oil and filter change at the time of sampling has been noted.

## HISTORICAL DIAGNOSIS

### 11 Sep 2023 Diag: Don Baldrige

NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report



### 19 Jun 2023 Diag: Wes Davis

NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report



### 01 Apr 2023 Diag: Don Baldrige

DIRT



Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor. All component wear rates are normal. Light fuel dilution occurring. Elemental level of silicon (Si) above normal. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.


view report





# OIL ANALYSIS REPORT

Sample Rating Trend



**WEAR**



Machine Id  
**728022-1149**

Component  
**Diesel Engine**

Fluid  
**CHEVRON DELO 400 XLE 15W40 (--- GAL)**

## DIAGNOSIS

### ▲ Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

### ▲ Wear

Cylinder, crank, or cam shaft wear is indicated. All other component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>GFL0096235</b>	GFL0064424	GFL0064377
Sample Date	Client Info	<b>06 Nov 2023</b>	11 Sep 2023	19 Jun 2023
Machine Age	hrs	<b>13681</b>	15450	14630
Oil Age	hrs	<b>0</b>	425	280
Oil Changed	Client Info	<b>Changed</b>	Not Changd	N/A
Sample Status		<b>ABNORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<b>&lt;1.0</b>	<1.0	<1.0
Glycol	WC Method	<b>NEG</b>	NEG	NEG

## WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >80	<b>▲ 103</b>	79	55
Chromium	ppm ASTM D5185m >5	<b>3</b>	2	1
Nickel	ppm ASTM D5185m >2	<b>2</b>	2	<1
Titanium	ppm ASTM D5185m	<b>8</b>	8	5
Silver	ppm ASTM D5185m >3	<b>0</b>	0	0
Aluminum	ppm ASTM D5185m >30	<b>9</b>	8	7
Lead	ppm ASTM D5185m >30	<b>&lt;1</b>	<1	0
Copper	ppm ASTM D5185m >150	<b>2</b>	2	<1
Tin	ppm ASTM D5185m >5	<b>&lt;1</b>	<1	0
Vanadium	ppm ASTM D5185m	<b>0</b>	<1	0
Cadmium	ppm ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m	<b>73</b>	64	155
Barium	ppm ASTM D5185m	<b>0</b>	0	4
Molybdenum	ppm ASTM D5185m	<b>88</b>	83	81
Manganese	ppm ASTM D5185m	<b>1</b>	1	<1
Magnesium	ppm ASTM D5185m	<b>752</b>	801	578
Calcium	ppm ASTM D5185m	<b>1686</b>	1855	1355
Phosphorus	ppm ASTM D5185m 760	<b>773</b>	782	595
Zinc	ppm ASTM D5185m 830	<b>992</b>	975	750
Sulfur	ppm ASTM D5185m 2770	<b>2881</b>	3631	2702

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >20	<b>19</b>	18	16
Sodium	ppm ASTM D5185m	<b>8</b>	9	6
Potassium	ppm ASTM D5185m >20	<b>8</b>	7	3

## INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	<b>1.1</b>	0.8	0.4
Nitration	Abs/cm *ASTM D7624 >20	<b>15.7</b>	13.4	10.6
Sulfation	Abs/.1mm *ASTM D7415 >30	<b>31.8</b>	26.9	23.6


## FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	<b>33.7</b>	26.4	20.7
Base Number (BN)	mg KOH/g ASTM D2896 10.7	<b>5.5</b>	6.0	7.6




# OIL ANALYSIS REPORT


### ▲ Ferrous Alloys



### Base Number



### Viscosity @ 100°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.9	15.8	15.0

### GRAPHS


#### ▲ Ferrous Alloys




#### Non-ferrous Metals



#### Viscosity @ 100°C



#### Base Number



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0096235 **Received** : 13 Nov 2023  
**Lab Number** : 06006081 **Diagnosed** : 15 Nov 2023  
**Unique Number** : 10739843 **Diagnostician** : Don Baldrige  
**Test Package** : FLEET

**GFL Environmental - 624 - Elmira Hauling**  
 10164 M-32  
 Elmira, MI  
 US 49730  
 Contact: ANDY GROBASKI  
 andyg@americanwaste.org  
 T: (989)370-2941  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)