




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
4564M
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0059149	GFL0086623	GFL0047598
Sample Date	Client Info	07 Nov 2023	23 Aug 2023	09 Mar 2022
Machine Age	hrs	8720	20754	17044
Oil Age	hrs	0	17044	15962
Oil Changed	Client Info	N/A	Changed	Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >3.0	<1.0	<1.0	<1.0
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >90	6	9	27
Chromium	ppm ASTM D5185m >20	<1	<1	1
Nickel	ppm ASTM D5185m >2	0	0	1
Titanium	ppm ASTM D5185m >2	0	0	<1
Silver	ppm ASTM D5185m >2	<1	0	<1
Aluminum	ppm ASTM D5185m >20	2	5	6
Lead	ppm ASTM D5185m >40	<1	0	<1
Copper	ppm ASTM D5185m >330	3	<1	1
Tin	ppm ASTM D5185m >15	0	<1	2
Antimony	ppm ASTM D5185m	---	---	---
Vanadium	ppm ASTM D5185m	0	0	<1
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	3	3	2
Barium	ppm ASTM D5185m 0	6	0	0
Molybdenum	ppm ASTM D5185m 60	61	63	57
Manganese	ppm ASTM D5185m 0	0	<1	<1
Magnesium	ppm ASTM D5185m 1010	855	1028	955
Calcium	ppm ASTM D5185m 1070	1033	1165	1090
Phosphorus	ppm ASTM D5185m 1150	996	1149	1064
Zinc	ppm ASTM D5185m 1270	1136	1386	1241
Sulfur	ppm ASTM D5185m 2060	3504	4014	2493

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	4	3	7
Sodium	ppm ASTM D5185m	0	10	5
Potassium	ppm ASTM D5185m >20	2	2	7

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >6	0.3	0.3	0.8
Nitration	Abs/cm *ASTM D7624 >20	7.3	7.8	11.4
Sulfation	Abs/.1mm *ASTM D7415 >30	18.3	19.1	24.3

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	14.0	15.3	21.5
Base Number (BN)	mg KOH/g ASTM D2896 9.8	8.4	8.8	6.5







OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	14.2

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0059149 Received : 14 Nov 2023
 Lab Number : 06006703 Diagnosed : 14 Nov 2023
 Unique Number : 10740465 Diagnostician : Wes Davis
 Test Package : FLEET

GFL Environmental - 415 - Michigan East
 6200 Elmridge
 Sterling Heights, MI
 US 48313
 Contact: Frank Wolak
 fwolak@gflenv.com
 T: (586)825-9514
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)