


## **OIL ANALYSIS REPORT**

### Sample Rating Trend









## Machine Id 4610M Component **Diesel Engine**

PETRO CANADA DURO

# **DIAGNOSIS**

#### Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


#### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sample Number   Client Info   GFL0059137   GFL0085042   GFL001842   Sample Date   Client Info   07 Nov 2023   17 Aug 2023   11 Mar 2022   Machine Age   hrs   Client Info   0   66726   0   Client Info   0   66726   0   Client Info   O   66726   0   Client Info   O   66726   0   Client Info   O   Changed   Changed	N SHP 15W40 (3	6 QTS)	Ma	2022	Aug2023 Nov20	23	
Sample Date	SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Machine Age   hrs   Client Info   Client Info   Coll Age   hrs   Client Info   Changed   Chang	Sample Number		Client Info		GFL0059137	GFL0085042	GFL0018428
Machine Age hrs Client Info 21272 83046 16320   Oil Age hrs Client Info 0 66726 0   Oil Changed Client Info Changed Changed Changed Changed   Sample Status NORMAL NORMAL NORMAL NORMAL NORMAL   CONTAMINATION method limit/base current history1 history2   Fuel WC Method 3.0 <1.0 <1.0 <1.0 <1.0   WEAR METALS method limit/base current history1 history2   fron ppm ASTM D5185m >90 26 23 10   Chromium ppm ASTM D5185m >20 3 <1	Sample Date		Client Info		07 Nov 2023	17 Aug 2023	11 Mar 2022
Dil Age	•	hrs	Client Info		21272	_	16320
Contact						66726	
NORMAL   NORMAL   NORMAL   NORMAL   CONTAMINATION   method   limit/base   current   history1   history2   history2     history2     history2     history2   history3   history	•				•		
WEAR METALS							
WEAR METALS method limit/base current history1 history2   Iron ppm ASTM D5185m >90 26 23 10   Chromium ppm ASTM D5185m >20 3 <1	CONTAMINAT	ION	method	limit/base	current	history1	history2
	Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Chromium	WEAR METAL	_S	method	limit/base	current	history1	history2
Nickel	Iron	ppm	ASTM D5185m	>90	26	23	10
Nicke    ppm   ASTM D5185m   >2   0   0   0   0   0   0   0   0   0	Chromium	ppm	ASTM D5185m	>20	3	<1	<1
Silver	Nickel		ASTM D5185m	>2	0		0
Silver							
Aluminum							
Lead							
Copper					_		
Trin							
Vanadium ppm ASTM D5185m 0 <1 0   Cadmium ppm ASTM D5185m 0 0 0   ADDITIVES method limit/base current history1 history2   Boron ppm ASTM D5185m 0 <1 2 4   Barium ppm ASTM D5185m 0 6 0 0 0   Molybdenum ppm ASTM D5185m 0 6 0 0 0   Manganese ppm ASTM D5185m 0 <1 <1 <1 <1   Magnesium ppm ASTM D5185m 1010 908 964 978   Calcium ppm ASTM D5185m 1070 1095 1118 1116   Phosphorus ppm ASTM D5185m 1270 1187 1252 1305   Sulfur ppm ASTM D5185m 2060 3267 3411 2618   CONTAMINANTS method limit/base	• •						
ADDITIVES				>15			
ADDITIVES		ppm					
Boron	Cadmium	ppm	ASTM D5185m		0	0	0
Barium	ADDITIVES		method	limit/base	current	history1	history2
Molybdenum ppm ASTM D5185m 60 64 60 59   Manganese ppm ASTM D5185m 0 <1	Boron	ppm	ASTM D5185m	0			4
Manganese ppm ASTM D5185m 0 <1 <1 <1   Magnesium ppm ASTM D5185m 1010 908 964 978   Calcium ppm ASTM D5185m 1070 1095 1118 1116   Phosphorus ppm ASTM D5185m 1150 1021 1025 1068   Zinc ppm ASTM D5185m 1270 1187 1252 1305   Sulfur ppm ASTM D5185m 2060 3267 3411 2618   CONTAMINANTS method limit/base current history1 history2   Silicon ppm ASTM D5185m 225 11 6 3   Sodium ppm ASTM D5185m >20 60 3 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol *ASTM D5185m >20 60 3 2   INFRA-RED method limit/base <td< td=""><td>Barium</td><td>ppm</td><td>ASTM D5185m</td><td>0</td><td>6</td><td>0</td><td>0</td></td<>	Barium	ppm	ASTM D5185m	0	6	0	0
Magnesium ppm ASTM D5185m 1010 908 964 978   Calcium ppm ASTM D5185m 1070 1095 1118 1116   Phosphorus ppm ASTM D5185m 1150 1021 1025 1068   Zinc ppm ASTM D5185m 1270 1187 1252 1305   Sulfur ppm ASTM D5185m 2060 3267 3411 2618   CONTAMINANTS method limit/base current history1 history2   Silicon ppm ASTM D5185m >25 11 6 3   Sodium ppm ASTM D5185m >20 60 3 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol % *ASTM D5185m >20 60 3 2   Glycol % *ASTM D5185m >20 NEG NEG   INFRA-RED method limit/base	Molybdenum	ppm	ASTM D5185m	60	64	60	59
Calcium ppm ASTM D5185m 1070 1095 1118 1116   Phosphorus ppm ASTM D5185m 1150 1021 1025 1068   Zinc ppm ASTM D5185m 1270 1187 1252 1305   Sulfur ppm ASTM D5185m 2060 3267 3411 2618   CONTAMINANTS method limit/base current history1 history2   Silicon ppm ASTM D5185m >25 11 6 3   Sodium ppm ASTM D5185m >20 60 3 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol "ASTM D5185m >20 60 3 2   INFRA-RED method limit/base current history1 history2   Soot % "ASTM D7844 >6 0.7 0.6 0.2   Nitration Abs/.1mm "ASTM D7415 >30 1	Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Calcium ppm ASTM D5185m 1070 1095 1118 1116   Phosphorus ppm ASTM D5185m 1150 1021 1025 1068   Zinc ppm ASTM D5185m 1270 1187 1252 1305   Sulfur ppm ASTM D5185m 2060 3267 3411 2618   CONTAMINANTS method limit/base current history1 history2   Silicon ppm ASTM D5185m >25 11 6 3   Sodium ppm ASTM D5185m >20 60 3 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol % *ASTM D2982 NEG NEG NEG   INFRA-RED method limit/base current history1 history2   Soot % % *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7414 <td< td=""><td>Magnesium</td><td>ppm</td><td>ASTM D5185m</td><td>1010</td><td>908</td><td>964</td><td>978</td></td<>	Magnesium	ppm	ASTM D5185m	1010	908	964	978
Phosphorus ppm ASTM D5185m 1150 1021 1025 1068   Zinc ppm ASTM D5185m 1270 1187 1252 1305   Sulfur ppm ASTM D5185m 2060 3267 3411 2618   CONTAMINANTS method limit/base current history1 history2   Silicon ppm ASTM D5185m >25 11 6 3   Sodium ppm ASTM D5185m >20 60 3 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol % *ASTM D5185m >20 60 3 2   Glycol % *ASTM D5982 NEG NEG NEG   INFRA-RED method limit/base current history1 history2   Soot % % *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30	Calcium	ppm	ASTM D5185m	1070	1095	1118	1116
Zinc	Phosphorus				1021	1025	1068
Sulfur ppm ASTM D5185m 2060 3267 3411 2618   CONTAMINANTS method limit/base current history1 history2   Silicon ppm ASTM D5185m >25 11 6 3   Sodium ppm ASTM D5185m 42 7 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol % *ASTM D5185m >20 60 3 2   MEG NEG NEG NEG NEG NEG   INFRA-RED method limit/base current history1 history2   Soot % % *ASTM D7844 >6 0.7 0.6 0.2   Nitration Abs/cm *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current hist			ASTM D5185m		1187		
Silicon ppm ASTM D5185m >25 11 6 3   Sodium ppm ASTM D5185m 42 7 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol % *ASTM D2982 NEG NEG NEG   INFRA-RED method limit/base current history1 history2   Soot % % *ASTM D7844 >6 0.7 0.6 0.2   Nitration Abs/cm *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	-						
Sodium ppm ASTM D5185m 42 7 2   Potassium ppm ASTM D5185m >20 60 3 2   Glycol % *ASTM D2982 NEG NEG NEG   INFRA-RED method limit/base current history1 history2   Soot % % *ASTM D7844 >6 0.7 0.6 0.2   Nitration Abs/cm *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	CONTAMINAN	NTS	method	limit/base	current	history1	history2
Potassium ppm ASTM D5185m >20 60 3 2   Glycol % *ASTM D2982 NEG NEG NEG   INFRA-RED method limit/base current history1 history2   Soot % % *ASTM D7844 >6 0.7 0.6 0.2   Nitration Abs/cm *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	Silicon	ppm	ASTM D5185m	>25	11	6	3
NEG   Nitration   Neg   Neg	Sodium	ppm	ASTM D5185m		42	7	2
INFRA-RED method limit/base current history1 history2   Soot % % *ASTM D7844 >6 0.7 0.6 0.2   Nitration Abs/cm *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	Potassium	ppm	ASTM D5185m	>20	60	3	2
Soot % % *ASTM D7844 >6 0.7 0.6 0.2   Nitration Abs/cm *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	Glycol	%	*ASTM D2982		NEG	NEG	NEG
Nitration Abs/cm *ASTM D7624 >20 7.8 10.8 8.4   Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	INFRA-RED		method	limit/base	current	history1	history2
Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	Soot %	%	*ASTM D7844	>6	0.7	0.6	0.2
Sulfation Abs/.1mm *ASTM D7415 >30 19.3 20.8 20.4   FLUID DEGRADATION method limit/base current history1 history2   Oxidation Abs/.1mm *ASTM D7414 >25 14.6 19.1 17.1	Vitration	Abs/cm	*ASTM D7624	>20	7.8	10.8	8.4
Oxidation							
	FLUID DEGRA	DATION	method	limit/base	current	history1	history2
	Oxidation	Abs/.1mm	*ASTM D7414	>25	14.6	19.1	17.1
	Base Number (BN)	mg KOH/g		9.8	8.7	7.6	10



## **OIL ANALYSIS REPORT**







Laboratory Sample No. Lab Number **Unique Number** 

: 06006706

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0059137

Received Diagnosed : 10740468

: 16 Nov 2023 Diagnostician

: Sean Felton

: 14 Nov 2023

Test Package : FLEET ( Additional Tests: Glycol ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GFL Environmental - 410 - Michigan West

39000 Van Born Rd Wayne, MI US 48184

Contact: Belal Dgheish bdgheish@gflenv.com T: (734)714-2340

Report Id: GFL410 [WUSCAR] 06006706 (Generated: 11/16/2023 08:40:14) Rev: 1

Submitted By: Belal Dgheish