

OIL ANALYSIS REPORT

Sample Rating Trend





DIAGNOSIS Recommendation

monitor. Wear

oil.

Contamination

Fluid Condition

Machine Id 913085

Fluid

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to

All component wear rates are normal.

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the

oil is acceptable for the time in service.

Component Diesel Engine

PETRO CANADA DURON SHP 15W40 (36 QTS)

		Sep202	3 Oct2023	Oct2023 N	ov2023	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0059139	GFL0059128	GFL008497
Sample Date		Client Info		07 Nov 2023	23 Oct 2023	04 Oct 2023
Machine Age	hrs	Client Info		3369	3229	3094
Oil Age	hrs	Client Info		0	3105	124
Oil Changed		Client Info		Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	25	10	87
Chromium	ppm	ASTM D5185m	>20	3	<1	3
Nickel	ppm	ASTM D5185m	>5	0	0	1
Titanium	ppm	ASTM D5185m	>2	<1	<1	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	31	6	5
Lead	ppm	ASTM D5185m	>40	<1	0	6
Copper	ppm	ASTM D5185m	>330	7	<1	2
Tin	ppm	ASTM D5185m	>15	<1	<1	1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<1	1	4
Barium	ppm	ASTM D5185m	0	6	0	0
Molybdenum	ppm	ASTM D5185m	60	61	51	63
Manganese	ppm	ASTM D5185m	0	<1	0	1
Magnesium	ppm	ASTM D5185m	1010	877	828	986
Calcium	ppm	ASTM D5185m	1070	1073	955	1123
Phosphorus	ppm	ASTM D5185m	1150	968	882	1095
Zinc	ppm	ASTM D5185m	1270	1160	1114	1356
Sulfur	ppm	ASTM D5185m	2060	3548	2521	2868
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	10	2	12
Sodium	ppm	ASTM D5185m		42	6	34
Potassium	ppm	ASTM D5185m	>20	59	18	4
Glycol	%	*ASTM D2982		NEG	NEG	NEG
INFRA-RED		method	limit/base	current	history1	history2
		*ASTM D7844	>4	0.7	0.2	1.5
Soot %	%	AO INI D7044		-		
Soot % Nitration	% Abs/cm	*ASTM D7624	>20	7.8	12.4	15.3
Soot % Nitration Sulfation	% Abs/cm Abs/.1mm	*ASTM D7624 *ASTM D7624	>20 >30	7.8 19.3	12.4 22.1	15.3 27.8
Soot % Nitration Sulfation FLUID DEGRAI	% Abs/cm Abs/.1mm DATION	*ASTM D7624 *ASTM D7624 *ASTM D7415 method	>20 >30 limit/base	7.8 19.3 current	12.4 22.1 history1	15.3 27.8 history2
Soot % Nitration Sulfation FLUID DEGRAD Oxidation	% Abs/cm Abs/.1mm DATION Abs/.1mm	*ASTM D7624 *ASTM D7624 *ASTM D7415 method *ASTM D7414	>20 >30 limit/base >25	7.8 19.3 current 14.7	12.4 22.1 history1 25.0	15.3 27.8 history2 29.3



OIL ANALYSIS REPORT



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: Belal Dgheish

F: