


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **227055-632109**

Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

		Feb2019	Dec2021 Feb2023	Jul2023 Aug2023 O	ct2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0098846	GFL0098807	GFL0090981
Sample Date		Client Info		06 Nov 2023	17 Oct 2023	26 Sep 2023
Machine Age	hrs	Client Info		6646	6489	6412
Oil Age	hrs	Client Info		0	20288	20288
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	17	21	15
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	4	4	<1
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m	>330	<1	3	1
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	2	4	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	57	62	63
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	947	999	1030
Calcium	ppm	ASTM D5185m	1070	982	1073	1081
Phosphorus	ppm	ASTM D5185m	1150	984	1092	1084
Zinc	ppm	ASTM D5185m	1270	1283	1326	1344
Sulfur	ppm	ASTM D5185m	2060	2932	3112	3281
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	7	6
Sodium	ppm	ASTM D5185m		<1	1	1
Potassium	ppm	ASTM D5185m	>20	<1	1	<1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.4	0.4	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.7	8.3	7.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5	18.5	18.6
	7100/.1111111					
FLUID DEGRA		method	limit/base	current	history1	history2
FLUID DEGRAD		method *ASTM D7414	limit/base	current	history1	history2
	DATION					



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	EKIIES	method	ilmit/base		nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	15.4	14.4	14.5	14.5

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10742589 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0098846 : 06008827

Received Diagnosed

: 15 Nov 2023 : 16 Nov 2023 Diagnostician : Wes Davis

GFL Environmental - 814 - Little Rock Hauling

4005 Hwy 161 N. Little Rock, AR US 72117

Contact: Brad Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: