


PROBLEM SUMMARY




1 Diesel Engine


PETRO CANADA DURON SHP 15W40 (7 GAL)






COMPONENT CONDITION SUMMARY







RECOMMENDATION

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS Sample Status NORMAL **ABNORMAL** Copper ASTM D5185m >100 **^** 70 ppm Silicon ppm ASTM D5185m >25 Visc @ 100°C cSt **11.2** ASTM D445 15.4 13.8

Customer Id: GFL405 Sample No.: GFL0097662 Lab Number: 06009340 Test Package: FLEET



To manage this report scan the QR code

To discuss the diagnosis or test data: Sean Felton +1 919-379-4092 sfelton@wearcheckusa.com

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Fluid			?	Oil and filter change at the time of sampling has been noted.
Change Filter			?	Oil and filter change at the time of sampling has been noted.

HISTORICAL DIAGNOSIS

21 Aug 2023 Diag: Wes Davis

NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.





OIL ANALYSIS REPORT






{UNASSIGNED} 711046

1 Diesel Engine

PETRO CANADA DURON SHP 15W40 (7 GAL)





DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

An increase in the copper level is noted. All other component wear rates are normal.

Contamination

Fuel content negligible. Elemental level of silicon (Si) above normal indicating ingress of seal material.

▲ Fluid Condition

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

ON SHP 15W4U (/ GAL)		Aug2023	Nov2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0097662	GFL0087295	
Sample Date		Client Info		04 Nov 2023	21 Aug 2023	
Machine Age	hrs	Client Info		4933	0	
Oil Age	hrs	Client Info		723	600	
Oil Changed		Client Info		Changed	Changed	
Sample Status				ABNORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>75	41	41	
Chromium	ppm	ASTM D5185m	>5	1	1	
Nickel	ppm	ASTM D5185m	>4	3	0	
Titanium	ppm	ASTM D5185m	>2	<1	0	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>15	3	4	
Lead	ppm	ASTM D5185m	>25	<1	0	
Copper	ppm	ASTM D5185m	>100	<u>^</u> 70	4	
Tin	ppm	ASTM D5185m	>4	3	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	47	4	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	60	91	68	
Manganese	ppm	ASTM D5185m	0	4	1	
Magnesium	ppm	ASTM D5185m	1010	728	1007	
Calcium	ppm	ASTM D5185m	1070	1294	1186	
Phosphorus	ppm	ASTM D5185m	1150	724	1088	
Zinc	ppm	ASTM D5185m	1270	936	1350	
Sulfur	ppm	ASTM D5185m	2060	2023	3545	
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	▲ 36	6	
Sodium	ppm	ASTM D5185m		6	4	
Potassium	ppm	ASTM D5185m	>20	4	<1	
Fuel	%	ASTM D3524	>3.0	0.5	<1.0	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>6	1	0.7	
Nitration	Abs/cm	*ASTM D7624	>20	12.1	9.3	
Sulfation					00.0	
	Abs/.1mm	*ASTM D7415	>30	24.2	20.8	
FLUID DEGRAI			>30 limit/base	24.2 current	20.8 history1	history2
FLUID DEGRAI						
	DATION	method	limit/base >25	current	history1	history2



OIL ANALYSIS REPORT

