


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
Sawmill/Canter
 Machine Id
[Sawmill^Canter] DLI HPU
 Component
Hydraulic System
 Fluid
PETRO CANADA HYDREX AW 68 (545 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The water content is negligible. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0111705	PCA0079400	PCA0079443
Sample Date	Client Info		13 Nov 2023	11 May 2023	14 Feb 2023
Machine Age	mths	Client Info	0	7	7
Oil Age	mths	Client Info	0	0	0
Oil Changed	Client Info		Not Changed	Changed	Filtered
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >20	0	0	<1
Chromium	ppm	ASTM D5185m >20	0	0	0
Nickel	ppm	ASTM D5185m >20	0	0	0
Titanium	ppm	ASTM D5185m	0	0	0
Silver	ppm	ASTM D5185m	0	0	0
Aluminum	ppm	ASTM D5185m >20	<1	1	0
Lead	ppm	ASTM D5185m >20	0	0	0
Copper	ppm	ASTM D5185m >20	<1	0	<1
Tin	ppm	ASTM D5185m >20	0	0	0
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	0	0	0
Barium	ppm	ASTM D5185m 0	7	0	0
Molybdenum	ppm	ASTM D5185m 0	<1	0	<1
Manganese	ppm	ASTM D5185m 0	0	0	0
Magnesium	ppm	ASTM D5185m 0	3	0	1
Calcium	ppm	ASTM D5185m 50	164	54	58
Phosphorus	ppm	ASTM D5185m 330	336	342	319
Zinc	ppm	ASTM D5185m 430	419	418	374
Sulfur	ppm	ASTM D5185m 760	1057	655	731

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	<1	<1	<1
Sodium	ppm	ASTM D5185m	0	0	<1
Potassium	ppm	ASTM D5185m >20	<1	0	0
Water	%	ASTM D6304 >0.05	0.015	0.004	0.006
ppm Water	ppm	ASTM D6304 >500	151.2	40.9	64.5






FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>5000	1411	1683	1713
Particles >6µm	ASTM D7647	>1300	160	300	485
Particles >14µm	ASTM D7647	>160	16	18	43
Particles >21µm	ASTM D7647	>40	6	6	10
Particles >38µm	ASTM D7647	>10	1	0	1
Particles >71µm	ASTM D7647	>3	0	0	0
Oil Cleanliness	ISO 4406 (c)	>19/17/14	18/14/11	18/15/11	18/16/13

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 0.60	0.36	0.40	0.23


OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	67.4	64.6	65.7

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0111705 **Received** : 16 Nov 2023
Lab Number : 06009651 **Diagnosed** : 17 Nov 2023
Unique Number : 10743413 **Diagnostician** : Wes Davis
Test Package : IND 2 (Additional Tests: KF)

West Fraser Inc. - Armour Lumber Mill
 361 Federal Road, PO Box 57
 Riegelwood, NC
 US 28456
 Contact: Lenore Popinchalk
 Lenore.Popinchalk@westfraser.com
 T:
 F: (910)655-9368

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)