

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area Walgreens - Tractor [Walgreens - Tractor] 136A63364

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| GAL) | | | | 0ct2023 | | |
|---------------|----------|-------------|------------|-------------|----------|----------|
| SAMPLE INFOR | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | PCA0105441 | | |
| Sample Date | | Client Info | | 30 Oct 2023 | | |
| Machine Age | mls | Client Info | | 62600 | | |
| Oil Age | mls | Client Info | | 17500 | | |
| Oil Changed | | Client Info | | Not Changd | | |
| Sample Status | | | | NORMAL | | |
| CONTAMINAT | ION | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >2.0 | <1.0 | | |
| Water | | WC Method | >0.2 | NEG | | |
| Glycol | | WC Method | | NEG | | |
| WEAR METAL | S | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 18 | | |
| Chromium | ppm | ASTM D5185m | >20 | 2 | | |
| Nickel | ppm | ASTM D5185m | >4 | 6 | | |
| Titanium | ppm | ASTM D5185m | | <1 | | |
| Silver | ppm | ASTM D5185m | >3 | <1 | | |
| Aluminum | ppm | ASTM D5185m | >20 | 17 | | |
| Lead | ppm | ASTM D5185m | >40 | 3 | | |
| Copper | ppm | ASTM D5185m | >330 | 11 | | |
| Tin | ppm | ASTM D5185m | >15 | 2 | | |
| Vanadium | ppm | ASTM D5185m | | 0 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 2 | 9 | | |
| Barium | ppm | ASTM D5185m | 0 | 0 | | |
| Molybdenum | ppm | ASTM D5185m | 50 | 59 | | |
| Manganese | ppm | ASTM D5185m | 0 | 1 | | |
| Magnesium | ppm | ASTM D5185m | 950 | 816 | | |
| Calcium | ppm | ASTM D5185m | 1050 | 1149 | | |
| Phosphorus | ppm | ASTM D5185m | 995 | 965 | | |
| Zinc | ppm | ASTM D5185m | 1180 | 1222 | | |
| Sulfur | ppm | ASTM D5185m | 2600 | 2959 | | |
| CONTAMINAN | TS | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 12 | | |
| Sodium | ppm | ASTM D5185m | | 0 | | |
| Potassium | ppm | ASTM D5185m | >20 | 44 | | |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.2 | | |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 7.8 | | |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 20.0 | | |
| FLUID DEGRAD | DATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 16.7 | | |
| Oxidation | | | | | | |




OIL ANALYSIS REPORT



Viscosity @ 100°C







: 10750996 Diagnostician Test Package : FLEET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: PCA0105441

:06011852

Received

Diagnosed

: 20 Nov 2023

: 21 Nov 2023

: Wes Davis

Laboratory

Sample No.

Lab Number

Unique Number