

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id
3736
Component
Diesel Engine
Fluid

MOBIL DELVAC 1300 SUPER15W40 (38 GAL

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SUPER15W40 (38 GAL)						
SAMPLE INFOR	AOITAMS	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0073223	GFL0073220	GFL008847
Sample Date		Client Info		16 Nov 2023	23 Oct 2023	13 Sep 2023
Machine Age	hrs	Client Info		16868	16763	16446
Oil Age	hrs	Client Info		650	650	600
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR META	LS	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>120	2	10	4
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	<1
Γitanium	ppm	ASTM D5185m	>2	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	2	6	2
_ead	ppm	ASTM D5185m	>40	0	1	1
Copper	ppm	ASTM D5185m	>330	<1	1	<1
Γin	ppm	ASTM D5185m	>15	<1	0	1
√anadium	ppm	ASTM D5185m		<1	0	<1
Cadmium	ppm	ASTM D5185m		0	0	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	447	205	349
Barium	ppm	ASTM D5185m	0	0	0	44
Molybdenum	ppm	ASTM D5185m	0	80	74	75
Manganese	ppm	ASTM D5185m		<1	0	1
Magnesium	ppm	ASTM D5185m	0	379	346	366
Calcium	ppm	ASTM D5185m		1408	1334	1241
Phosphorus	ppm	ASTM D5185m		1064	869	936
Zinc	ppm	ASTM D5185m		1293	1173	1168
Sulfur	ppm	ASTM D5185m		3305	2509	3481
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	10	6
Sodium	ppm	ASTM D5185m		2	8	2
Potassium	ppm	ASTM D5185m	>20	<1	2	4
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.1	0.4	0.1
Vitration	Abs/cm	*ASTM D7624	>20	5.5	8.0	6.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.9	23.5	19.0
FLUID DEGRA	ADATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	19.1	12.9
Dogo Nurskar (DAI)		ACTM DOCCO	0.4	7.0	Г 1	7 4


Base Number (BN) mg KOH/g ASTM D2896 9.4

7.8



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2	
Visc @ 100°C	cSt	ASTM D445	14	13.9	12.6	13.8	

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10751102 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0073223 : 06011958

Received Diagnosed

: 20 Nov 2023 : 21 Nov 2023 Diagnostician : Sean Felton

GFL Environmental - 146 - Augusta

1064 Franke Industrial Augusta, GA US 30909

Contact: JEFFERY WASHINGTON jeff.washington@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: