

## **OIL ANALYSIS REPORT**

Sample Rating Trend



# 727091-310016

Component Transmission (Auto)

PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)

## DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the fluid.

## Fluid Condition


The condition of the fluid is acceptable for the time in service.

			GUILOLO	1012020		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0100497	GFL0065225	
Sample Date		Client Info		13 Nov 2023	26 Jan 2023	
Machine Age	hrs	Client Info		15374	171360	
Oil Age	hrs	Client Info		15374	0	
Oil Changed		Client Info		Changed	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINAT		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>160	36	37	
Chromium	ppm	ASTM D5185m	>5	0	0	
Nickel	ppm	ASTM D5185m	>5	0	<1	
Titanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m	>5	0	0	
Aluminum	ppm		>50	22	11	
Lead	ppm	ASTM D5185m		0	<1	
Copper	ppm	ASTM D5185m		30	34	
Tin	ppm	ASTM D5185m		<1	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
	pp		11 11 11		-	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		76	75	
Barium	ppm	ASTM D5185m		0	0	
Molybdenum	ppm	ASTM D5185m		<1	1	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m		3	3	
Calcium	ppm	ASTM D5185m		124	131	
Phosphorus	ppm	ASTM D5185m		217	248	
Zinc	ppm	ASTM D5185m		8	26	
Sulfur	ppm	ASTM D5185m		1713	1797	
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	5	10	
Sodium	ppm	ASTM D5185m		1	4	
Potassium	ppm	ASTM D5185m	>20	3	1	
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
Emuismed water	Jouran	riodadi	20.1	NEG	NEG	
Free Water	scalar	*Visual	20.1	NEG	NEG	

Submitted By: TECHNICIAN ACCOUNT



# **OIL ANALYSIS REPORT**



	FLUID PROPE	ERTIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	34	32.6	33.1	
	SAMPLE IMA	GES	method	limit/base	current	history1	history2
	Color				no image	no image	no image
Nov13/23	Bottom				no image	no image	no image
	GRAPHS						
	Ferrous Alloys	als		Nov13/23			
551 (d0°C)	Viscosity @ 40°C			Mov13/23			
Laboratory Sample No.	: WearCheck USA - : GFL0100497	501 Madis Received Diagnose	1 02 : <b>1</b>	lov 2023		ironmental - 865 - E '213 East Mount	Houston Roa
Lab Number Unique Number Unique Number Test Package discuss this sample report, co Denotes test methods that ar tements of conformity to specif	e outside of the ISO	ician : Sea 200-237-1369 pe of accred	Houston, T US 7709 Contact: Saul Casti saul.castillo@gflenv.co JCGM 106:2012)				

Submitted By: TECHNICIAN ACCOUNT