


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



725004

Component

Transmission (Auto)

PETRO CANADA DuraDrive HD Synthetic 668 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

668 (QTS)								
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		GFL0097942	GFL0097917	GFL0094372		
Sample Date		Client Info		15 Nov 2023	12 Oct 2023	22 Sep 2023		
Machine Age	hrs	Client Info		9983	9829	9698		
Oil Age	hrs	Client Info		431	277	146		
Oil Changed	0	Client Info		Not Changd	Not Changd	Not Changd		
Sample Status				NORMAL	NORMAL	NORMAL		
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2		
Water		WC Method	>0.1	NEG	NEG	NEG		
WEAR METAL	_S	method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>160	134	72	73		
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1		
Nickel	ppm	ASTM D5185m	>5	0	0	0		
Titanium	ppm	ASTM D5185m		0	0	0		
Silver	ppm	ASTM D5185m	>5	0	0	0		
Aluminum	ppm	ASTM D5185m		42	28	30		
Lead	ppm	ASTM D5185m	>50	10	2	2		
Copper	ppm	ASTM D5185m		26	12	14		
Tin	ppm	ASTM D5185m	>10	8	2	2		
Vanadium	ppm	ASTM D5185m	>10	<1	0	0		
Cadmium		ASTM D5185m		0	0	0		
	ppm							
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		53	66	65		
Barium	ppm	ASTM D5185m		0	0	0		
Molybdenum	ppm	ASTM D5185m		<1	<1	1		
Manganese	ppm	ASTM D5185m		2	<1	2		
Magnesium	ppm	ASTM D5185m		0	2	5		
Calcium	ppm	ASTM D5185m		114	124	128		
Phosphorus	ppm	ASTM D5185m		181	208	224		
Zinc	ppm	ASTM D5185m		0	0	8		
Sulfur	ppm	ASTM D5185m		1636	1888	1660		
CONTAMINA	NTS	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>20	7	9	10		
Sodium	ppm	ASTM D5185m		6	1	9		
Potassium	ppm	ASTM D5185m	>20	4	3	4		
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG		
Free Water	scalar	*Visual		NEG	NEG	NEG		
-26-20\ Dov: 1	Joalal	Violai			Submitted Dv: IC			





OIL ANALYSIS REPORT




FLUID PROPI	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	34	32.3	32.1	31.9
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

GRAPHS











Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10752022 Test Package : FLEET

: GFL0097942 : 06012878

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 20 Nov 2023 Diagnosed : 22 Nov 2023 Diagnostician : Jonathan Hester

GFL Environmental - 010 - Stockbridge

1280 Rum Creek Parkway Stockbridge, GA US 30281

Contact: JOSHUA TINKER

joshuatinker@gflenv.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: