


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **438683**

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)			Jul2023	Nov2023		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0110492	PCA0103064	
Sample Date		Client Info		07 Nov 2023	21 Jul 2023	
Machine Age	mls	Client Info		19112	12683	
Oil Age	mls	Client Info		0	0	
Oil Changed		Client Info		Changed	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	78	89	
Chromium	ppm	ASTM D5185m	>20	2	2	
Nickel	ppm	ASTM D5185m	>4	<1	1	
Titanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>20	17	13	
Lead	ppm	ASTM D5185m	>40	<1	<1	
Copper	ppm	ASTM D5185m	>330	27	33	
Tin	ppm	ASTM D5185m	>15	4	4	
Vanadium	ppm	ASTM D5185m		<1	<1	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	20	42	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	45	43	
Manganese	ppm	ASTM D5185m	0	9	12	
Magnesium	ppm	ASTM D5185m	950	675	590	
Calcium	ppm	ASTM D5185m	1050	1599	1833	
Phosphorus	ppm	ASTM D5185m	995	808	782	
Zinc	ppm	ASTM D5185m	1180	1030	989	
Sulfur	ppm	ASTM D5185m	2600	2405	2862	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	10	13	
Sodium	ppm	ASTM D5185m		6	8	
Potassium	ppm	ASTM D5185m	>20	29	21	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6	0.4	
Nitration	Abs/cm	*ASTM D7624	>20	11.1	10.7	
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.1	24.6	
FLUID DEGRAD	OITAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	23.2	24.1	
Base Number (BN)	mg KOH/g	ASTM D2896		8.5	8.9	



OIL ANALYSIS REPORT







Laboratory Sample No. Lab Number **Unique Number**

: PCA0110492 : 06012990 : 10752134

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 20 Nov 2023 Diagnosed : 21 Nov 2023 Diagnostician : Wes Davis

Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MILLER TRUCK LEASING #119

39 INDUSTRIAL AVE HASBROUCK HEIGHTS, NJ US 07604

Contact: MIKE LONGETTE mlongette@millertransgroup.com

T:

F: (201)528-7053