


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
FORD 625 (S/N 1FM5K8AR6DGB15819)

Component
Gasoline Engine

Fluid
PETRO CANADA SUPREME 5W20 MOTOR OIL (6 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

| | method | limit/base | current | history1 | history2 |
|---------------|-------------|-------------|--------------------|-------------|----------|
| Sample Number | Client Info | | PCA0105354 | PCA0097978 | --- |
| Sample Date | Client Info | | 10 Nov 2023 | 29 Jun 2023 | --- |
| Machine Age | mls | Client Info | 89903 | 88419 | --- |
| Oil Age | mls | Client Info | 1484 | 1620 | --- |
| Oil Changed | Client Info | | Changed | Changed | --- |
| Sample Status | | | NORMAL | NORMAL | --- |

CONTAMINATION

| | method | limit/base | current | history1 | history2 |
|--------|-----------|------------|----------------|----------|----------|
| Fuel | WC Method | >4.0 | <1.0 | <1.0 | --- |
| Water | WC Method | >0.2 | NEG | NEG | --- |
| Glycol | WC Method | | NEG | NEG | --- |

WEAR METALS

| | method | limit/base | current | history1 | history2 |
|----------|--------|------------------|--------------|----------|----------|
| Iron | ppm | ASTM D5185m >150 | 4 | 5 | --- |
| Chromium | ppm | ASTM D5185m >20 | <1 | 0 | --- |
| Nickel | ppm | ASTM D5185m >5 | <1 | 0 | --- |
| Titanium | ppm | ASTM D5185m | <1 | <1 | --- |
| Silver | ppm | ASTM D5185m >2 | 0 | 0 | --- |
| Aluminum | ppm | ASTM D5185m >40 | 2 | 1 | --- |
| Lead | ppm | ASTM D5185m >50 | <1 | 0 | --- |
| Copper | ppm | ASTM D5185m >155 | 7 | 3 | --- |
| Tin | ppm | ASTM D5185m >10 | 0 | 0 | --- |
| Vanadium | ppm | ASTM D5185m | 0 | <1 | --- |
| Cadmium | ppm | ASTM D5185m | <1 | 0 | --- |

ADDITIVES

| | method | limit/base | current | history1 | history2 |
|------------|--------|------------------|--------------|----------|----------|
| Boron | ppm | ASTM D5185m 183 | 67 | 139 | --- |
| Barium | ppm | ASTM D5185m 0 | 9 | 0 | --- |
| Molybdenum | ppm | ASTM D5185m 36 | 67 | 61 | --- |
| Manganese | ppm | ASTM D5185m 0 | <1 | <1 | --- |
| Magnesium | ppm | ASTM D5185m 417 | 503 | 472 | --- |
| Calcium | ppm | ASTM D5185m 1318 | 1225 | 1253 | --- |
| Phosphorus | ppm | ASTM D5185m 773 | 711 | 685 | --- |
| Zinc | ppm | ASTM D5185m 845 | 810 | 800 | --- |
| Sulfur | ppm | ASTM D5185m 2690 | 3205 | 3118 | --- |

CONTAMINANTS

| | method | limit/base | current | history1 | history2 |
|-----------|--------|------------------|-----------|----------|----------|
| Silicon | ppm | ASTM D5185m >30 | 19 | 18 | --- |
| Sodium | ppm | ASTM D5185m >400 | 3 | 6 | --- |
| Potassium | ppm | ASTM D5185m >20 | 2 | <1 | --- |



INFRA-RED

| | method | limit/base | current | history1 | history2 |
|-----------|----------|-----------------|-------------|----------|----------|
| Soot % | % | *ASTM D7844 | 0 | 0.1 | --- |
| Nitration | Abs/cm | *ASTM D7624 >20 | 8.1 | 7.8 | --- |
| Sulfation | Abs/.1mm | *ASTM D7415 >30 | 18.3 | 17.5 | --- |

FLUID DEGRADATION

| | method | limit/base | current | history1 | history2 |
|------------------|----------|-----------------|-------------|----------|----------|
| Oxidation | Abs/.1mm | *ASTM D7414 >25 | 13.2 | 11.2 | --- |
| Base Number (BN) | mg KOH/g | ASTM D2896 6.5 | 3.3 | 4.9 | --- |









OIL ANALYSIS REPORT



| VISUAL | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | --- |
| Yellow Metal | scalar | *Visual | NONE | NONE | --- |
| Precipitate | scalar | *Visual | NONE | NONE | --- |
| Silt | scalar | *Visual | NONE | NONE | --- |
| Debris | scalar | *Visual | NONE | NONE | --- |
| Sand/Dirt | scalar | *Visual | NONE | NONE | --- |
| Appearance | scalar | *Visual | NORML | NORML | --- |
| Odor | scalar | *Visual | NORML | NORML | --- |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | --- |
| Free Water | scalar | *Visual | | NEG | --- |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| Visc @ 100°C | cSt | ASTM D445 | 8.42 | 8.1 | --- |

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0105354 **Received** : 20 Nov 2023
Lab Number : 06013195 **Diagnosed** : 21 Nov 2023
Unique Number : 10752339 **Diagnostician** : Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

VILLAGE OF NORTH RIVERSIDE
 2345 S DESPLAINES
 NORTH RIVERSIDE, IL
 US 60546
 Contact: Service Manager
 vznrpdw@gmail.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: