


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
KEMP QUARRIES / HULBERT
 Machine Id
WL085
 Component
Diesel Engine
 Fluid
MOBIL DELVAC 1300 SUPER15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PCA0109247	PCA0061826	PCA0048671
Sample Date	Client Info	11 Nov 2023	08 Nov 2022	11 Feb 2022
Machine Age	hrs	28114	27587	27117
Oil Age	hrs	0	0	0
Oil Changed	Client Info	Changed	Changed	Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >100	46	56	44
Chromium	ppm ASTM D5185m >20	<1	<1	<1
Nickel	ppm ASTM D5185m >4	1	<1	<1
Titanium	ppm ASTM D5185m	0	0	0
Silver	ppm ASTM D5185m >3	0	0	0
Aluminum	ppm ASTM D5185m >20	2	0	0
Lead	ppm ASTM D5185m >40	4	4	7
Copper	ppm ASTM D5185m >330	4	8	11
Tin	ppm ASTM D5185m >15	<1	0	2
Antimony	ppm ASTM D5185m	---	---	---
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	2	2	5
Barium	ppm ASTM D5185m 0	0	0	0
Molybdenum	ppm ASTM D5185m 0	50	49	67
Manganese	ppm ASTM D5185m	<1	<1	0
Magnesium	ppm ASTM D5185m 0	819	773	932
Calcium	ppm ASTM D5185m	1299	1617	1214
Phosphorus	ppm ASTM D5185m	1079	998	1048
Zinc	ppm ASTM D5185m	1214	1275	1414
Sulfur	ppm ASTM D5185m	3068	3606	2200

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	3	2	4
Sodium	ppm ASTM D5185m	2	1	0
Potassium	ppm ASTM D5185m >20	1	0	0



INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	1.5	2.1	0.9
Nitration	Abs/cm *ASTM D7624 >20	8.7	9.4	8.2
Sulfation	Abs/.1mm *ASTM D7415 >30	21.2	22.9	20.1

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	15.7	15.1	15.4
Base Number (BN)	mg KOH/g ASTM D2896 9.4	8.8	9.6	9.1










OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14	13.6	13.4	14.0

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0109247 **Received** : 24 Nov 2023
Lab Number : 06017108 **Diagnosed** : 28 Nov 2023
Unique Number : 10756252 **Diagnostician** : Sean Felton
Test Package : MOB 1 (Additional Tests: TBN)

Kemp Quarries - Kemp Stone - Hulbert
 17801 Hwy 80
 Hulbert, OK
 US 74441
 Contact:
 hulbert@kempstone.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: