OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
928069-260339
Component
Transmission (Auto)
Fluid
PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the fluid.

Fluid Condition
The condition of the fluid is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**GFL0098630**	GFL0083769	GFL0033972
Sample Date		Client Info		**17 Nov 2023**	07 Jun 2023	05 May 2022
Machine Age	hrs	Client Info		**13602**	13142	11063
Oil Age	hrs	Client Info		**0**	13142	1300
Oil Changed		Client Info		**N/A**	Not Changd	Not Changd
Sample Status				**NORMAL**	ABNORMAL	ATTENTION

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>160	**49**	44	44
Chromium	ppm	ASTM D5185m	>5	**<1**	0	0
Nickel	ppm	ASTM D5185m	>5	**<1**	0	0
Titanium	ppm	ASTM D5185m		**<1**	0	0
Silver	ppm	ASTM D5185m	>5	**0**	0	<1
Aluminum	ppm	ASTM D5185m	>50	**18**	14	14
Lead	ppm	ASTM D5185m	>50	**7**	7	10
Copper	ppm	ASTM D5185m	>225	**14**	11	9
Tin	ppm	ASTM D5185m	>10	**2**	1	1
Vanadium	ppm	ASTM D5185m		**0**	0	0
Cadmium	ppm	ASTM D5185m		**<1**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**90**	90	116
Barium	ppm	ASTM D5185m		**0**	0	0
Molybdenum	ppm	ASTM D5185m		**1**	0	0
Manganese	ppm	ASTM D5185m		**<1**	<1	<1
Magnesium	ppm	ASTM D5185m		**8**	<1	0
Calcium	ppm	ASTM D5185m		**104**	112	80
Phosphorus	ppm	ASTM D5185m		**209**	264	285
Zinc	ppm	ASTM D5185m		**0**	4	6
Sulfur	ppm	ASTM D5185m		**1459**	1533	968

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	**6**	4	5
Sodium	ppm	ASTM D5185m		**5**	6	3
Potassium	ppm	ASTM D5185m	>20	**2**	2	0

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	▲ MODER	▲ MODER
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

OIL ANALYSIS REPORT





FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	34	**32.84**	33.0	33.2

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			*no image*	*no image*	*no image*
Bottom			*no image*	*no image*	*no image*

GRAPHS







Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0098630 **Received** : 24 Nov 2023
Lab Number : 06017216 **Diagnosed** : 01 Dec 2023
Unique Number : 10756360 **Diagnostician** : Jonathan Hester
Test Package : FLEET (Additional Tests: FT-IR, KV100)

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GFL Environmental - 836 - Kansas City Hauling
7801 East Truman Road
Kansas City, MO
US 64126
Contact: Robert Hart
rhart@gflenv.com
T: (580)461-1509
F: