

## **OIL ANALYSIS REPORT**

Sample Rating Trend





### Machine Id MACK 2305

Component Diesel Engine Fluid

DURALENE Dura-Tech Syn Blend 10W40 (--- GAL)

## DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

Metal levels are typical for a new component breaking in.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

/n Blend 10W40 (-	GAL)			Nov2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0096094		
Sample Date		Client Info		21 Nov 2023		
Machine Age	mls	Client Info		64044		
Oil Age	mls	Client Info		17044		
Oil Changed	1110	Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron		ASTM D5185m	>120	10		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm ppm	ASTM D5185m	>20 >5	3		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>2	۰ <1		
Aluminum	ppm	ASTM D5185m	>20	4		
Lead	ppm	ASTM D5185m	>40	 0		
Copper	ppm		>330	<1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m	210	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		2		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		55		
Manganese	ppm	ASTM D5185m		<1		
Vagnesium	ppm	ASTM D5185m		918		
Calcium	ppm	ASTM D5185m		1049		
Phosphorus	ppm	ASTM D5185m		1094		
Zinc	ppm	ASTM D5185m		1239		
Sulfur	ppm	ASTM D5185m		2990		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	8		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	7		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.4		
Nitration	Abs/cm	*ASTM D7624	>20	9.4		
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8		
FLUID DEGRAI	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.4		
Base Number (BN)	mg KOH/g	ASTM D2896		6.8		
	- 0					



13 Abnormal 12. 11 Nov21/23

# **OIL ANALYSIS REPORT**



	VISUAL		method	limit/base	current	history1	history2	
	White Metal	scalar *	Visual	NONE	NONE			
	Yellow Metal	scalar *	Visual	NONE	NONE			
	Precipitate	scalar *	Visual	NONE	NONE			
	Silt	scalar *	Visual	NONE	NONE			
	Debris	scalar *	Visual	NONE	NONE			
	Sand/Dirt	scalar *	Visual	NONE	NONE			
20 2 2 2 2 2	Appearance	scalar *	Visual	NORML	NORML			
Movi	Odor	scalar *	Visual	NORML	NORML			
С	Emulsified Water	scalar *	Visual	>0.2	NEG			
	Free Water	scalar *	Visual		NEG			
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2	
	Visc @ 100°C	cSt A	STM D445		13.4			
	GRAPHS							
	Ferrous Alloys							
	iron			-				
	8 - newspace chromium							
	6							
	Edd							
	4							
	2							
	0							
	Vov21/23			Nov21/23				
	≥ Non-ferrous Metal	le		Z				
	copper							
	8 - the second s							
	6-							
	m dd							
	4							
	2							
	23	********	*********	/23				
	Nov21/23			Nov21/23				
	 Viscosity @ 100°C	2			De la Nuella			
	18			7.0 T	Base Number			
	17 Abnormal			6.0-				
	16							
	Q 15			9.0 24.0				
	(2-115- 115- 115- 115- 115-			L. T.O.				
				(B,HD) HD) Jacobi Jacob				
	Abnormal							
	12-			1.0				
	114				53+		23 +	
	Vov21,			Vov21	Vov21.		Nov21/23	
	_							
	: WearCheck USA - 5				Z FOR			
Sample No.				: 27 Nov 2023 : 28 Nov 2023			OE ORR RE HEIGHTS II	
				Davis		CHICAGO	US 6041	
Certificate L2367 Test Package	e : FLEET	-				Contact: MIKE PROCANIN		
					mprocan	in@zforcetransp		
					CCM 106-0010		T: F:	
Sample No. Lab Number Unique Numbe	: WearCheck USA - 5 : PCA0096094 : 06017740 er : 10756884 e : FLEET t, contact Customer Serve are outside of the ISO 1	Received Diagnosed Diagnostici vice at 1-800 7025 scope	: 27 N : 28 N ian : Wes 0-237-1369 e of accredi	ry, NC 27513 lov 2023 lov 2023 bov 2023 bov s bavis	mprocan	700 E J CHICAGO Contact: MIKE	OE ORF HEIGHT US 60 PROCA	