


# **OIL ANALYSIS REPORT**

Sample Rating Trend



NORMAL



Machine Id 3695 Component

**Transmission (Auto)** 

PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)

# DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the fluid.


## **Fluid Condition**

The condition of the fluid is acceptable for the time in service.

668 ( GAL)  Oct. 100 Cot. 1								
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		GFL0101243	GFL0086108	GFL0086098		
Sample Date		Client Info		04 Dec 2023	25 Jul 2023	01 Jul 2023		
Machine Age	hrs	Client Info		1839	17215	17071		
Oil Age	hrs	Client Info		932	1432	1065		
Oil Changed		Client Info		Changed	Not Changd	Not Changd		
Sample Status				NORMAL	NORMAL	NORMAL		
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2		
Water		WC Method	>0.1	NEG	NEG	NEG		
WEAR METAI	_S	method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>160	106	101	97		
Chromium	ppm	ASTM D5185m	>5	<1	<1	0		
Nickel	ppm	ASTM D5185m	>5	<1	0	<1		
Titanium	ppm	ASTM D5185m		0	0	0		
Silver	ppm	ASTM D5185m	>5	0	0	<1		
Aluminum	ppm	ASTM D5185m	>50	11	12	9		
Lead	ppm	ASTM D5185m	>50	1	0	1		
Copper	ppm	ASTM D5185m	>225	8	7	7		
Tin	ppm	ASTM D5185m	>10	<1	<1	1		
Vanadium	ppm	ASTM D5185m		0	0	0		
Cadmium	ppm	ASTM D5185m		0	0	0		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		56	57	66		
Barium	ppm	ASTM D5185m		0	0	0		
Molybdenum	ppm	ASTM D5185m		<1	<1	<1		
Manganese	ppm	ASTM D5185m		1	2	2		
Magnesium	ppm	ASTM D5185m		2	2	2		
Calcium	ppm	ASTM D5185m		136	140	143		
Phosphorus	ppm	ASTM D5185m		211	227	214		
Zinc	ppm	ASTM D5185m		0	3	6		
Sulfur	ppm	ASTM D5185m		1746	2002	1669		
CONTAMINA	NTS	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>20	12	13	12		
Sodium	ppm	ASTM D5185m		2	5	0		
Potassium	ppm	ASTM D5185m	>20	2	1	3		
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG		
Free Water	scalar	*Visual		NEG	NEG	NEG		





# **OIL ANALYSIS REPORT**




FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	34	31.4	31.5	31.6
SAMPLE IMAG	ES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

### **GRAPHS**











Laboratory Sample No. Lab Number Unique Number : 10776726 Test Package : FLEET

: GFL0101243 : 06026935

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 06 Dec 2023 Received Diagnosed : 08 Dec 2023 Diagnostician : Don Baldridge

GFL Environmental - 010 - Stockbridge 1280 Rum Creek Parkway

Stockbridge, GA US 30281

Contact: JOSHUA TINKER joshuatinker@gflenv.com

T: F:

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)