

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



FREIGHTLINER 822045 - URN28

Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (---

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM Sample Number	MATION					
Sample Number		method		current	history1	history2
oumpic reamber		Client Info		GFL0091665	GFL0036645	
Sample Date		Client Info		01 Dec 2023	28 Apr 2023	
Machine Age	hrs	Client Info		61058	4352	
Oil Age	hrs	Client Info		250	600	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	ATTENTION	
CONTAMINATI	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	▲ 3.6	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METALS	6	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	29	64	
Chromium	ppm	ASTM D5185m	>5	<1	<1	
Nickel	ppm	ASTM D5185m	>2	0	0	
Titanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>30	3	4	
Lead	ppm	ASTM D5185m	>30	0	0	
Copper	ppm	ASTM D5185m	>150	1	5	
Tin	ppm	ASTM D5185m	>5	0	0	
Vanadium	ppm	ASTM D5185m		<1	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	4	24	
Barium	ppm	ASTM D5185m	0	0	2201	
Molybdenum	ppm	ASTM D5185m	60	62	34	
Manganese	ppm	ASTM D5185m	0	<1	2	
Magnesium	ppm	ASTM D5185m	1010	973	491	
Calcium	ppm	ASTM D5185m	1070	1212	1138	
Phosphorus	ppm	ASTM D5185m	1150	1083	866	
Zinc	ppm	ASTM D5185m	1270	1335	810	
Sulfur	ppm	ASTM D5185m	2060	3026	2627	
CONTAMINAN	ΓS	method	limit/base	current	history1	history2
Silicon	ppm		>20	5	18	
Sodium	ppm	ASTM D5185m		7	23	
Potassium	ppm	ASTM D5185m	>20	4	19	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.9	0.6	
Nitration	Abs/cm	*ASTM D7624	>20	10.7	11.1	
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.9	33.0	
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.6	38.9	
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.7	12.4	



OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPE	RTIES	method	limit/base	current	history1	history2

14.0

11.8

Visc @	100°C
GBA	рце




cSt


ASTM D445 15.4



Non-ferrous Metals

Viscosity @ 100°C









Laboratory Sample No. Lab Number Unique Number : 10776917 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0091665 Received Diagnosed : 06027126

: 06 Dec 2023 : 11 Dec 2023 Diagnostician : Jonathan Hester GFL Environmental - 036 - North Wilksboro 489 Boone Trail

Wilkesboro, NC US 28659

Contact: JAMES KRESGE jkresge@gflenv.com

T:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: