


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
613282

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0099669	PCA0077034	---
Sample Date	Client Info		21 Sep 2023	26 Aug 2022	---
Machine Age	mls	Client Info	103838	0	---
Oil Age	mls	Client Info	20000	10000	---
Oil Changed	Client Info		Changed	Changed	---
Sample Status			NORMAL	ABNORMAL	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	---
Water	WC Method	>0.2	NEG	NEG	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	19	▲ 108	---
Chromium	ppm	ASTM D5185m >20	<1	17	---
Nickel	ppm	ASTM D5185m >4	<1	0	---
Titanium	ppm	ASTM D5185m	1	<1	---
Silver	ppm	ASTM D5185m >3	0	<1	---
Aluminum	ppm	ASTM D5185m >20	4	87	---
Lead	ppm	ASTM D5185m >40	<1	<1	---
Copper	ppm	ASTM D5185m >330	9	▲ 687	---
Tin	ppm	ASTM D5185m >15	<1	9	---
Vanadium	ppm	ASTM D5185m	0	0	---
Cadmium	ppm	ASTM D5185m	<1	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	213	16	---
Barium	ppm	ASTM D5185m 0	0	0	---
Molybdenum	ppm	ASTM D5185m 50	44	10	---
Manganese	ppm	ASTM D5185m 0	1	6	---
Magnesium	ppm	ASTM D5185m 950	13	711	---
Calcium	ppm	ASTM D5185m 1050	2036	1330	---
Phosphorus	ppm	ASTM D5185m 995	1133	734	---
Zinc	ppm	ASTM D5185m 1180	1337	855	---
Sulfur	ppm	ASTM D5185m 2600	3849	2859	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	14	8	---
Sodium	ppm	ASTM D5185m	4	7	---
Potassium	ppm	ASTM D5185m >20	8	217	---



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.4	0.6	---
Nitration	Abs/cm	*ASTM D7624 >20	10.6	16.5	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	21.4	27.4	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	19.4	28.6	---
Base Number (BN)	mg KOH/g	ASTM D2896	4.7	6.2	---









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	11.4

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0099669 **Received** : 07 Dec 2023
Lab Number : 06027340 **Diagnosed** : 11 Dec 2023
Unique Number : 10777131 **Diagnostician** : Jonathan Hester
Test Package : MOB 1 (Additional Tests: TBN)

MILLER TRUCK LEASING #121
 107 HOW LANE
 NEW BRUNSWICK, NJ
 US 08901
 Contact: Anthony Cursi
 acursi@millertransgroup.com
 T: (732)358-4027
 F: (732)400-8475

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)