


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **521034**

Component **Diesel Engine**

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

āAL)		Jun202	3 Jul2023	Sep 2023 D	ec2023	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0086923	GFL0086935	GFL0087002
Sample Date		Client Info		04 Dec 2023	06 Sep 2023	06 Jul 2023
Machine Age	hrs	Client Info		6900	6501	6208
Oil Age	hrs	Client Info		692	293	600
Oil Changed		Client Info		N/A	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR META	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	3	13	6
Chromium	ppm	ASTM D5185m	>20	0	1	<1
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>20	<1	4	2
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	4	8	6
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	55	66	63
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	959	1033	916
Calcium	ppm	ASTM D5185m	1070	870	1165	1114
Phosphorus	ppm	ASTM D5185m	1150	855	1112	1020
Zinc	ppm	ASTM D5185m	1270	1086	1352	1181
Sulfur	ppm	ASTM D5185m	2060	2854	3932	2941
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3	5	3
Sodium	ppm	ASTM D5185m		<1	4	0
Potassium	ppm	ASTM D5185m	>20	0	15	4
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2	0.5	0.3
Nitration	Abs/cm	*ASTM D7624	>20	5.3	7.4	6.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.6	18.1	18.7
FLUID DEGRA	ADATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.1	13.1	13.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.9	8.2	8.9



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.3	13.4	

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10778317 Test Package : FLEET

: GFL0086923 : 06028526

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 07 Dec 2023 Diagnosed : 09 Dec 2023 Diagnostician : Wes Davis

GFL Environmental - 408 - Brown City 4235 M-53

BROWN CITY, MI US 48416

Contact: MARK WOMBLE

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: