

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

SENNEBOGEN 840E MH-82

Front Right Planetary Fluid GEAR OIL SAE 80W90 (--- LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Nov2023		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0112785		
Sample Date		Client Info		16 Nov 2023		
Machine Age	hrs	Client Info		230		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATI	ON	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	304		
Chromium	ppm	ASTM D5185m	>10	2		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>75	47		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	0		
Barium	ppm	ASTM D5185m	200	342		
Molybdenum	ppm	ASTM D5185m	12	0		
Manganese	ppm	ASTM D5185m		7		
Magnesium	ppm	ASTM D5185m	12	2		
Calcium	ppm	ASTM D5185m	150	9		
Phosphorus	ppm	ASTM D5185m	1650	1129		
Zinc	ppm	ASTM D5185m	125	40		
Sulfur	ppm	ASTM D5185m	22500	28599		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	4		
Sodium	ppm	ASTM D5185m	>170	4		
Potassium	ppm	ASTM D5185m	>20	2		
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	2.00	1.26		



Base 130 120 Abnormal 110 Nov16/23

OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
v	White Metal	scalar	*Visual	NONE	MODER		
Y	ellow Metal	scalar	*Visual	NONE	NONE		
F	Precipitate	scalar	*Visual	NONE	NONE		
5	Silt	scalar	*Visual	NONE	NONE		
E	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
A Nov16/23	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
F	Free Water	scalar	*Visual		NEG		
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2
١	/isc @ 40°C	cSt	ASTM D445	143	183		
	SAMPLE IMAG	ES	method	limit/base	current	history1	history2
Nov16/23	Color				no image	no image	no image
No							
	Dettern						
E	Bottom				no image	no image	no image
	GRAPHS						
					Load (nnm)		
2000	Iron (ppm)			15			
톱 1000-	Severe			E ¹⁰	0 - Severe		
4,1000	Abnormal				Abnormal		
0.	123						
	Nov16/23			Nov16/23	Nov16/23		
	– Aluminum (ppm)			-	Chromium (p	om)	
100-				3	⁰ Severe		
톱 50	1			u 1	0 - Abnormal		
д.	Abnormal						
0.	6/23						
	Nov16/23			Nov16/23	Nov16/23		
	– Copper (ppm)				 Silicon (ppm)		
200				30	⁰ I e		
톱 100				²⁰ 10	0 - Severe		
- 0.				-10	0 Abnormal		
0.	Nov16/23			Nov16/23	Nav16/23		
	Novi			Nov1	Nov1		
	Viscosity @ 40°C			(B/H	Acid Number		
200- ç;	Abnormal			/23 Acid Number (mg KOH/g) 	Abnormal		
(D-0+) 150- ts				ц га 2	0 Base Abnormal		*****
3 100-	Abnormal				0 L		
	16/2:			/16/23 Aci	/16/23		
	Nov			Nov	Nov		
100	WearCheck USA - 5	501 Madis Received		Nov16	Nov16	ETAL SERVICES (SM 250 WES	S Mill Services LI T U.S. HWY
Sample No.		neceiveu					ESTERTON, I
Sample No. : Lab Number : (PCA0112785	Diagnose		Dec 2023		CHE	
Sample No. : Lab Number : (Jnique Number :	PCA0112785 06028773 10778564			Dec 2023 s Davis			US 4630
Sample No. : Lab Number : (Unique Number : Test Package :	PCA0112785 I 06028773 I 10778564 I MOB 2	Diagnose Diagnosti	i cian : We	s Davis	du.	Contact: DC	US 4630 MINIC WHIT
Sample No.: ILab Number: 0Unique Number: 0Test Package: 1sample report, con	PCA0112785 06028773 10778564	Diagnose Diagnosti ice at 1-80	i cian :We	s Davis 9.	dv		US 4630 MINIC WHIT



Contact/Location: DOMINIC WHITE - SCRBURIN