

# **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

## Machine Id 423020-864

Component

# Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

## DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


GAL)		May2021	Jan2022 Jun2022	Dec2022 Jun2023	Dec2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0100050	GFL0062197	GFL0062227
Sample Date		Client Info		04 Dec 2023	05 Sep 2023	06 Jun 2023
Machine Age	hrs	Client Info		23532	23484	23041
Oil Age	hrs	Client Info		493	445	21323
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	28	22	41
Chromium	ppm	ASTM D5185m	>20	<1	1	2
Nickel	ppm		>4	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	3	2
Lead	ppm	ASTM D5185m	>40	1	3	8
Copper	ppm	ASTM D5185m	>330	<1	<1	1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	10	12	8
Barium	ppm	ASTM D5185m	0	3	0	0
Molybdenum	ppm	ASTM D5185m	60	65	63	73
Manganese	ppm			0	1	<1
Magnesium	ppm	ASTM D5185m	1010	881	1013	1030
Calcium	ppm	ASTM D5185m	1070	1116	1251	1228
Phosphorus	ppm	ASTM D5185m	1150	993	1093	1135
Zinc	ppm	ASTM D5185m	1270	1210	1418	1386
Sulfur	ppm	ASTM D5185m	2060	3077	3908	3572
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	6	6
Sodium	ppm	ASTM D5185m		4	6	7
Potassium	ppm	ASTM D5185m	>20	4	4	4
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.5	0.7
Nitration	Abs/cm	*ASTM D7624	>20	10.5	9.3	11.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.2	21.2	23.4
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.2	17.0	19.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.9	7.8	7.7



# **OIL ANALYSIS REPORT**



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	13.8	13.9
GRAPHS						
Ferrous Alloys						



Submitted By: GARY BREWER