

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id 300607

Component Diesel Engine

Fluid PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| Oil Age Oil Changed Sample Status CONTAMINATIO | MATION mls mls | method Client Info Client Info Client Info Client Info | limit/base | current PCA0104254 | history1 PCA0102999 | history2 PCA0094225 |
|---|----------------------|--|--------------|-----------------------|------------------------|------------------------|
| Sample Date Machine Age Oil Age Oil Changed Sample Status CONTAMINATIO | | Client Info Client Info Client Info | | | | PCA0094225 |
| Machine Age Oil Age Oil Changed Sample Status CONTAMINATIO | | Client Info Client Info | | | | |
| Oil Age Oil Changed Sample Status CONTAMINATIC | | Client Info | | 11 Nov 2023 | 15 Aug 2023 | 20 Mar 2023 |
| Oil Changed Sample Status CONTAMINATIC Fuel | mls | | | 28482 | 25077 | 22064 |
| Sample Status CONTAMINATIO | | Client Info | | 0 | 0 | 0 |
| CONTAMINATIC Fuel | | | | Changed | Not Changd | Not Changd |
| Fuel | | | | NORMAL | NORMAL | NORMAL |
| | NC | method | limit/base | current | history1 | history2 |
| Alsten . | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | ; | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 19 | 15 | 7 |
| Chromium | ppm | ASTM D5185m | >20 | 1 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >4 | <1 | 0 | 0 |
| | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 10 | 6 | 3 |
| | ppm | ASTM D5185m | >40 | 0 | <1 | 0 |
| | ppm | ASTM D5185m | >330 | 5 | 4 | 2 |
| | ppm | | >15 | <1 | <1 | 0 |
| | ppm | ASTM D5185m | | 0 | <1 | 0 |
| | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| | ppm | | 2 | 12 | 14 | 16 |
| | ppm | ASTM D5185m | 0 | 0 | 0 | 0 |
| • | ppm | ASTM D5185m | 50 | 61 | 62 | 54 |
| - | ppm | ASTM D5185m | 0 | <1 | <1 | <1 |
| - | ppm | ASTM D5185m | 950 | 872 | 916 | 797 |
| | ppm | ASTM D5185m | 1050 | 1105 | 1149 | 1014 |
| | ppm | ASTM D5185m ASTM D5185m | 995 | 1019 | 987 1232 | 895 1075 |
| • •• | ppm ppm | ASTM D5185m | 1180 2600 | 1238 3134 | 3618 | 3409 |
| CONTAMINANT | | method | limit/base | current | history1 | history2 |
| | ppm | ASTM D5185m | >25 | 3 | 4 | 3 |
| | ppm | ASTM D5185m | | 2 | 2 | <1 |
| | ppm | ASTM D5185m | >20 | 6 | 5 | 3 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.7 | 0.4 | 0.2 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 9.3 | 7.5 | 6.0 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 19.3 | 18.1 | 17.8 |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 15.5 | 13.9 | 13.1 |
| | mg KOH/g | ASTM D2896 | | 8.2 | 8.8 | 9.6 |



OIL ANALYSIS REPORT





Certificate L2367

Laboratory

Sample No.

Contact/Location: MIKE LONGETTE - MILRUT