

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

TS)		0ct2022	Dec2022	Feb2023 May2023	Sep2023	
SAMPLE INFOF	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0103366	PCA0099760	PCA0092860
Sample Date		Client Info		13 Sep 2023	29 May 2023	27 Feb 2023
Achine Age	mls	Client Info		109271	84508	63537
Dil Age	mls	Client Info		45734	20971	46463
Dil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	SEVERE	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
uel		WC Method	>5	<1.0	<1.0	<1.0
Vater		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>100	27	13	28
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
lickel	ppm	ASTM D5185m	>4	1	0	<1
Titanium	ppm	ASTM D5185m		1	1	6
Silver	ppm	ASTM D5185m	>3	0	1	<1
Aluminum	ppm	ASTM D5185m	>20	6	3	10
ead	ppm	ASTM D5185m	>40	2	5	2
Copper	ppm	ASTM D5185m	>330	243	4 19	159
in	ppm	ASTM D5185m	>15	2	<1	3
/anadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	1	7
Barium	ppm	ASTM D5185m	0	0	0	0
/lolybdenum	ppm	ASTM D5185m	50	58	56	56
/anganese	ppm	ASTM D5185m	0	<1	<1	1
/lagnesium	ppm	ASTM D5185m	950	875	878	755
Calcium	ppm	ASTM D5185m	1050	1075	1029	1111
hosphorus	ppm	ASTM D5185m	995	849	948	750
Zinc	ppm	ASTM D5185m	1180	1149	1172	990
Sulfur	ppm	ASTM D5185m	2600	2653	2646	2682
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	5	7
Sodium	ppm	ASTM D5185m		4	2	4
Potassium	ppm	ASTM D5185m	>20	18	10	27
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.3	0.5
Nitration	Abs/cm	*ASTM D7624	>20	10.3	8.6	9.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.4	19.3	21.4
		method	limit/base	current	history1	history2
FLUID DEGRA	BAHON					
FLUID DEGRA	Abs/.1mm	*ASTM D7414	>25	17.4	15.1	17.0




OIL ANALYSIS REPORT

Ferrous Alloys



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	10.8	11.0	10.6
GRAPHS						



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

F: