


# **OIL ANALYSIS REPORT**

## Sample Rating Trend







# Machine Id **2026867**

Component

2 Differential

GEAR OIL SAE 80W90 (--- QTS)

## DIAGNOSIS

## Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.


## **Fluid Condition**

The condition of the oil is acceptable for the time in service.

		Jul2020 D	ec2020 Aug2021 Dec	2021 May2022 Sep2022	May2023	
SAMPLE INFOF	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0103345	PCA0099769	PCA0095202
Sample Date		Client Info		06 Aug 2023	30 May 2023	27 Mar 2023
Machine Age	mls	Client Info		336391	311808	291746
Oil Age	mls	Client Info		336391	311808	291746
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	TION	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG	NEG	NEG
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	207	205	195
Chromium	ppm	ASTM D5185m	>10	2	2	2
Nickel	ppm	ASTM D5185m	>10	5	5	6
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	2	3
Lead	ppm	ASTM D5185m	>25	2	0	0
Copper	ppm	ASTM D5185m	>100	6	5	3
Tin	ppm	ASTM D5185m	>10	0	0	1
Vanadium	ppm	ASTM D5185m	7.0	<1	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	PPIII	method	limit/base	current	history1	history2
					•	
Boron	ppm	ASTM D5185m	400	250	249	242 1
Barium	ppm	ASTM D5185m	200	0	0	
Molybdenum	ppm	ASTM D5185m	12	0	0	<1
Manganese	ppm	ASTM D5185m	4.0	10	10	11
Magnesium	ppm	ASTM D5185m	12	0	0	4
Calcium	ppm	ASTM D5185m	150	0	0	7
Phosphorus	ppm	ASTM D5185m	1650	1302	1322	1385
Zinc	ppm	ASTM D5185m	125	0	0	12
Sulfur	ppm	ASTM D5185m	22500	24655	25426	28842
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	35	27	26
Sodium	ppm	ASTM D5185m	>170	6	6	6
Potassium	ppm	ASTM D5185m	>20	10	0	3
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	LIGHT	LIGHT	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
0:50:05\ Day: 1						Submitted Dur





## **OIL ANALYSIS REPORT**




FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	143	103	103	103
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

## **GRAPHS**









Laboratory Sample No. Test Package : FLEET

Lab Number Unique Number : 10781797

: PCA0103345 : 06032006

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 11 Dec 2023

Diagnosed : 14 Dec 2023

Diagnostician : Sean Felton

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact: ROBERT LOCKWOOD Robert.Lockwood@Perdue.com

**PERDUE FARMS - GEORGETOWN** 

T: F:

20621 SAVANAH RD

GEORGETOWN, DE

Report Id: PERGEODE [WUSCAR] 06032006 (Generated: 12/15/2023 08:52:05) Rev: 1

Submitted By: ?

US 19947