OIL DIAGNOSTICS

PROBLEM SUMMARY

Sample Rating Trend



DIRT

Area
FLEET
Machine Id
Volvo 2126935
Component
1 Differential
Fluid
GEAR OIL SAE 75W90 (--- GAL)

COMPONENT CONDITION SUMMARY



RECOMMENDATION

No corrective action is recommended at this time.
Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS

Sample Status				**ABNORMAL**	NORMAL	---
Silicon	ppm	ASTM D5185m	>75	▲ **117**	59	---

Customer Id: PERDILSC
Sample No.: PCA0108081
Lab Number: 06032537
Test Package: FLEET

To manage this report scan the QR code

To discuss the diagnosis or test data:
Don Baldridge +1
don.b505@comcast.net

To change component or sample information:
Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

RECOMMENDED ACTIONS

There are no recommended actions for this sample.

HISTORICAL DIAGNOSIS

16 Aug 2023 Diag: Don Baldridge

NORMAL

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

view report

OIL ANALYSIS REPORT

Sample Rating Trend



DIRT

Area
FLEET
Machine Id
Volvo 2126935
Component
1 Differential
Fluid
GEAR OIL SAE 75W90 (--- GAL)

DIAGNOSIS

Recommendation
No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
Elemental level of silicon (Si) above normal indicating ingress of dirt/seal material.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0108081**	PCA0102048	---
Sample Date		Client Info		**03 Dec 2023**	16 Aug 2023	---
Machine Age	hrs	Client Info		**0**	0	---
Oil Age	hrs	Client Info		**0**	0	---
Oil Changed		Client Info		**N/A**	N/A	---
Sample Status				**ABNORMAL**	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>.2	**NEG**	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	**360**	177	---
Chromium	ppm	ASTM D5185m	>10	**4**	3	---
Nickel	ppm	ASTM D5185m	>10	**4**	5	---
Titanium	ppm	ASTM D5185m		**<1**	<1	---
Silver	ppm	ASTM D5185m		**0**	0	---
Aluminum	ppm	ASTM D5185m	>25	**2**	2	---
Lead	ppm	ASTM D5185m	>25	**6**	0	---
Copper	ppm	ASTM D5185m	>100	**62**	0	---
Tin	ppm	ASTM D5185m	>10	**4**	<1	---
Vanadium	ppm	ASTM D5185m		**0**	0	---
Cadmium	ppm	ASTM D5185m		**0**	0	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	**112**	146	---
Barium	ppm	ASTM D5185m	200	**6**	2	---
Molybdenum	ppm	ASTM D5185m	12	**0**	0	---
Manganese	ppm	ASTM D5185m		**14**	13	---
Magnesium	ppm	ASTM D5185m	12	**1**	2	---
Calcium	ppm	ASTM D5185m	150	**15**	24	---
Phosphorus	ppm	ASTM D5185m	1650	**1125**	1042	---
Zinc	ppm	ASTM D5185m	125	**19**	25	---
Sulfur	ppm	ASTM D5185m	22500	**25037**	27116	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	▲ **117**	59	---
Sodium	ppm	ASTM D5185m		**9**	6	---
Potassium	ppm	ASTM D5185m	>20	**2**	2	---

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	---
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	---
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	---
Silt	scalar	*Visual	NONE	**NONE**	NONE	---
Debris	scalar	*Visual	NONE	**LIGHT**	NONE	---
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	---
Appearance	scalar	*Visual	NORML	**NORML**	NORML	---
Odor	scalar	*Visual	NORML	**NORML**	NORML	---
Emulsified Water	scalar	*Visual	>.2	**NEG**	NEG	---
Free Water	scalar	*Visual		**NEG**	NEG	---

OIL ANALYSIS REPORT

Silicon (ppm)



Viscosity @ 40°C

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	109	**93.5**	94.8	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			*no image*	*no image*	*no image*
Bottom			*no image*	*no image*	*no image*

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0108081 **Recieved** : 12 Dec 2023
Lab Number : 06032537 **Diagnosed** : 15 Dec 2023
Unique Number : 10782328 **Diagnostician** : Don Baldridge
Test Package : FLEET

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

PERDUE FARMS - DILLON
2047 HWY 9 WEST
DILLON, SC
US 29536
Contact: KEVIN HOOKS
kevin.hooks@perdue.com
T: (843)841-8069
F: (843)841-8070