

# **OIL ANALYSIS REPORT**

Sample Rating Trend



### Area **FLEET** Machine Id **2227075 (S/N 4v4nc9eh0rv631481)**

#### Component 2 Differential

Fluid GEAR OIL SAE 75W90 (--- GAL)

## DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


# Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFOR	ΜΑΤΙΟΝ	method	limit/base	current	history1	history2
			in the babb			
Sample Number		Client Info		PCA0108136		
Sample Date	la va	Client Info		03 Dec 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG		
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	138		
Chromium	ppm	ASTM D5185m	>10	2		
Nickel	ppm	ASTM D5185m	>10	2		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>100	<1		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	154		
Barium	ppm	ASTM D5185m	200	0		
Molybdenum	ppm	ASTM D5185m	12	0		
Manganese	ppm	ASTM D5185m		10		
Magnesium	ppm	ASTM D5185m	12	<1		
Calcium	ppm	ASTM D5185m	150	15		
Phosphorus	ppm	ASTM D5185m	1650	1144		
Zinc	ppm	ASTM D5185m	125	12		
Sulfur	ppm	ASTM D5185m	22500	25187		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	37		
Sodium	ppm	ASTM D5185m		4		
Potassium	ppm	ASTM D5185m	>20	2		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
O de a	scalar	*Visual	NORML	NORML		
Udor	0000.00					
Emulsified Water	scalar	*Visual	>.2	NEG		
Odor Emulsified Water Free Water						



# **OIL ANALYSIS REPORT**



FLUID PR	OPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	109	96.7		
SAMPLE I	IMAGES	method	limit/base	current	history1	history2
			[		y	
Color				no image	no image	no image
				no inago	no imago	no inago
Dec3/23						
Bottom				no image	no image	no image
GRAPHS						
Ferrous Alloy	ys					
140 iron	1					
120 - anatomiu	m					
100						
80						
60						
40						
0						
Dec3/23			Dec3/23 -			
			Dei			
Non-ferrous	Metals					
9 - copper						
8 <b>-</b> tin 7 -						
6-						
Ē. 5						
3						
2						
			22			
Dec3/23			Dec3/23			
Viscosity @ 4	40°C					
135 130 Abnormal			, -			
125 -						
120						
ਹਿ 110 - <b>Base</b> ਲੁੱ 105 -	*****	*****	******			
형 105						
95 -						
90 - Abnormal						
80			23			
Dec3/23			Dec3/23			
N/a a cola a la la		A C		0		
very : WearCheck U No. : PCA0108136	Recieved		ry, NC 2751 Dec 2023	3		<b>RMS - DILLO</b> 7 HWY 9 WES
nber : 06032539	Diagnos		Dec 2023			DILLON, S
Number : 10782330 ackage : FLEET	Diagnost	tician : Dor	1 Baldridge		Contact:	US 2953 KEVIN HOOK
report, contact Custome					kevin.hook	s@perdue.co
ds that are outside of the				( ICOM 100.0010		(843)841-806

To discuss this sample \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

F: (843)841-8070