




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
809M
 Component
Gasoline Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0105655	GFL0064050	---
Sample Date	Client Info		11 Dec 2023	12 Dec 2022	---
Machine Age	hrs	Client Info	26835	24519	---
Oil Age	hrs	Client Info	24519	0	---
Oil Changed	Client Info		Changed	Changed	---
Sample Status			NORMAL	NORMAL	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>4.0	<1.0	<1.0	---
Water	WC Method	>0.2	NEG	NEG	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >150	32	27	---
Chromium	ppm	ASTM D5185m >20	<1	<1	---
Nickel	ppm	ASTM D5185m >5	0	0	---
Titanium	ppm	ASTM D5185m	0	0	---
Silver	ppm	ASTM D5185m >2	0	1	---
Aluminum	ppm	ASTM D5185m >40	<1	1	---
Lead	ppm	ASTM D5185m >50	<1	1	---
Copper	ppm	ASTM D5185m >155	<1	1	---
Tin	ppm	ASTM D5185m >10	0	<1	---
Vanadium	ppm	ASTM D5185m	0	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	1	3	---
Barium	ppm	ASTM D5185m 0	0	0	---
Molybdenum	ppm	ASTM D5185m 60	54	63	---
Manganese	ppm	ASTM D5185m 0	<1	<1	---
Magnesium	ppm	ASTM D5185m 1010	976	894	---
Calcium	ppm	ASTM D5185m 1070	1048	1145	---
Phosphorus	ppm	ASTM D5185m 1150	1010	1036	---
Zinc	ppm	ASTM D5185m 1270	1214	1253	---
Sulfur	ppm	ASTM D5185m 2060	2784	3078	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >30	5	3	---
Sodium	ppm	ASTM D5185m >400	2	0	---
Potassium	ppm	ASTM D5185m >20	0	1	---

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0.2	0.2	---
Nitration	Abs/cm	*ASTM D7624 >20	11.2	10.8	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	22.8	22.8	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	24.8	23.1	---
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	6.3	8.8	---







OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	12.9	12.7	---

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0105655 **Received** : 13 Dec 2023
Lab Number : **06033164** **Diagnosed** : 15 Dec 2023
Unique Number : 10782955 **Diagnostician** : Don Baldrige
Test Package : FLEET

GFL Environmental - 415 - Michigan East
 6200 Elmridge
 Sterling Heights, MI
 US 48313
 Contact: Frank Wolak
 fwolak@gflenv.com
 T: (586)825-9514
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)