


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **26543**

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QTS)		Feb2021	May2021 Oct2021 Dec20	21 Apr2022 Oct2022 Apr2023	Nov2023	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0112395	PCA0092873	PCA0080580
Sample Date		Client Info		15 Nov 2023	16 Apr 2023	10 Oct 2022
Machine Age	mls	Client Info		0	641766	591740
Oil Age	mls	Client Info		40000	21000	20000
Oil Changed		Client Info		Changed	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	66	23	40
Chromium	ppm	ASTM D5185m	>20	1	<1	<1
Nickel	ppm	ASTM D5185m	>4	2	<1	2
Titanium	ppm	ASTM D5185m		3	2	3
Silver	ppm	ASTM D5185m	>3	<1	<1	<1
Aluminum	ppm	ASTM D5185m	>20	7	2	3
Lead	ppm	ASTM D5185m	>40	3	<1	2
Copper	ppm	ASTM D5185m	>330	11	4	9
Tin	ppm	ASTM D5185m	>15	<1	<1	1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	<1	4	2
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	59	59	54
Manganese	ppm	ASTM D5185m	0	1	<1	<1
Magnesium	ppm	ASTM D5185m	950	905	936	841
Calcium	ppm	ASTM D5185m	1050	1085	1147	1165
Phosphorus	ppm	ASTM D5185m	995	932	1027	904
Zinc	ppm	ASTM D5185m	1180	1210	1279	1198
Sulfur	ppm	ASTM D5185m	2600	2907	3780	3131
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	7	4	6
Sodium	ppm	ASTM D5185m		17	9	21
Potassium	ppm	ASTM D5185m	>20	7	2	6
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.9	0.4	0.6
Nitration	Abs/cm	*ASTM D7624	>20	10.2	8.5	10.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.3	19.6	22.4
FLUID DEGRAI	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.3	15.6	17.8
Base Number (BN)	mg KOH/g	ASTM D2896		4.9	7.9	7



OIL ANALYSIS REPORT








VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method			history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.0	11.3	10.9

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10791884 Test Package : FLEET

: PCA0112395 : 06036655

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 15 Dec 2023 Diagnosed : 19 Dec 2023

Diagnostician : Angela Borella

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Contact: ROBERT LOCKWOOD Robert.Lockwood@Perdue.com

PERDUE FARMS - GEORGETOWN

T:

20621 SAVANAH RD

GEORGETOWN, DE

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) US 19947

F: