

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **2126971 - 2nd** Component

Rear Differential

Fluid PETRO CANADA TRAXON SYNTHETIC 75W90 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0108192		
Sample Date		Client Info		14 Nov 2023		
Machine Age	mls	Client Info		57348		
Oil Age	mls	Client Info		57348		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINAT		method	limit/base	current	history1	history2
Water			>.2	NEG		
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	89		
Chromium	ppm		>10	1		
Nickel	ppm	ASTM D5185m	>10	5		
Titanium	ppm	ASTM D5185m	210	ر <1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>25	1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>100	4		
Tin	ppm	ASTM D5185m	>100	۔ <1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	328	267		
Barium	ppm	ASTM D5185m	1	0		
Molybdenum	ppm	ASTM D5185m		2		
Manganese	ppm	ASTM D5185m		12		
Magnesium	ppm	ASTM D5185m	1	2		
Calcium	ppm	ASTM D5185m	7	16		
Phosphorus	ppm	ASTM D5185m	1145	948		
Zinc	ppm	ASTM D5185m	3	2		
Sulfur	ppm	ASTM D5185m	17909	23112		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	27		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	5		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Free Water	scalar	*Visual		NEG		
8:58:25) Rev: 1			Contact/I	ocation: ROBE		



OIL ANALYSIS REPORT



FL	UID PROPE	RTIES	method	limit/base	current	history1	history2
Visc	@ 40°C	cSt	ASTM D445	99.6	116		
SA	MPLE IMAG	GES	method	limit/base	current	history1	history2
Colo	r				no image	no image	no image
Botto	om				no image	no image	no image
GF	RAPHS						
Fer	rous Alloys						
80 -	iron chromium						
70 -	nickel						
60							
50- 40-							
30 20							
10-							
0							
Nov14/23				Nov14/23			
No 10 T	n-ferrous Meta	ls					
9-	copper						
8 7							
6 - Ed. 5 -							
4-							
3							
1							
Nov14/23				Nov14/23			
				Nov			
140 T :	cosity @ 40°C						
130 -	ormal						
120-							
() 110 () 00 () 100 () 100 () 100							
ਤੋਂ 100 - Bas	e			****			
90 -							
	ormal						
70 + 723				4/23			
Nov14/23				Nov14/23			
: PCA : 0603 er : 1079	37120 92349	501 Madis Recieved Diagnose Diagnosti	:15 d:20	ary, NC 2751 Dec 2023 Dec 2023 nathan Heste	r		SAVANAH IGETOWN, US 199
port, contact	Customer Serv					Robert.Lockwood	@Perdue.co
	ide of the ISO 1 s are based on t				(ICGM 106:2012	2)	

To discuss this sample * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

F: