

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL





Machine Id **795M** Component **Diesel Engine**

PETRO CANADA DURON SHP 15W40 (36 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

N SHP 15W40 (36	GAL)	Ma	r2022	Dec2023 Dec20	23		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		GFL0104226	GFL0059294	GFL0018499	
Sample Date		Client Info		12 Dec 2023	07 Dec 2023	28 Mar 2022	
Machine Age	hrs	Client Info		8098	8101	6355	
Oil Age	hrs	Client Info		0	8101	0	
Oil Changed		Client Info		N/A	Changed	N/A	
Sample Status				NORMAL	ABNORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2	
-uel		WC Method	>3.0	<1.0	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	NEG	
Glycol		WC Method		NEG	NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2	
ron	ppm	ASTM D5185m	>75	7	40	30	
Chromium	ppm	ASTM D5185m	>5	<1	2	1	
Nickel	ppm	ASTM D5185m	>4	<1	0	0	
Γitanium	ppm	ASTM D5185m	>2	0	0	0	
Silver	ppm	ASTM D5185m	>2	0	0	0	
Aluminum	ppm	ASTM D5185m	>15	2	3	1	
_ead	ppm	ASTM D5185m	>25	0	1	<1	
Copper	ppm	ASTM D5185m	>100	<1	3	2	
Γin	ppm	ASTM D5185m	>4	<1	0	<1	
/anadium	ppm	ASTM D5185m		0	0	0	
Cadmium	ppm	ASTM D5185m		0	0	0	
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	0	1	<1	4	
Barium	ppm	ASTM D5185m		0	0	0	
Molybdenum	ppm	ASTM D5185m	60	52	53	67	
Manganese	ppm	ASTM D5185m		<1	<1	<1	
Magnesium	ppm	ASTM D5185m	1010	889	949	1103	
Calcium	ppm	ASTM D5185m	1070	967	1028	1236	
Phosphorus	ppm	ASTM D5185m	1150	973	1001	1209	
Zinc	ppm	ASTM D5185m	1270	1218	1190	1496	
Sulfur	ppm	ASTM D5185m	2060	2956	2729	2608	
CONTAMINAN	TS	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	2	7	4	
Sodium	ppm	ASTM D5185m		1	38	3	
Potassium	ppm	ASTM D5185m	>20	2	1	2	
INFRA-RED		method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>6	0.3	1	0.4	
Vitration	Abs/cm	*ASTM D7624	>20	6.7	13.5	12.0	
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.9	24.8	24.2	
FLUID DEGRADATION method limit/base current history1 history2							
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	25.2	21.7	
- Aldation							



13


OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method			history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.9	13.4	14.4

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10792515

: 06037286

: GFL0104226 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 18 Dec 2023 Diagnosed : 18 Dec 2023

Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GFL Environmental - 410 - Michigan West

39000 Van Born Rd Wayne, MI US 48184

Contact: Belal Dgheish bdgheish@gflenv.com T: (734)714-2340