




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
{UNASSIGNED}

Machine Id
Autocar

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0103597	GFL0085310	---
Sample Date	Client Info	11 Dec 2023	12 Jul 2023	---
Machine Age	hrs Client Info	0	0	---
Oil Age	hrs Client Info	595	0	---
Oil Changed	Client Info	N/A	N/A	---
Sample Status		NORMAL	NORMAL	---

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	---
Water	WC Method >0.2	NEG	NEG	---
Glycol	WC Method	NEG	NEG	---

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >100	32	6	---
Chromium	ppm ASTM D5185m >20	1	<1	---
Nickel	ppm ASTM D5185m >4	<1	0	---
Titanium	ppm ASTM D5185m	<1	0	---
Silver	ppm ASTM D5185m >3	0	0	---
Aluminum	ppm ASTM D5185m >20	8	3	---
Lead	ppm ASTM D5185m >40	1	0	---
Copper	ppm ASTM D5185m >330	7	<1	---
Tin	ppm ASTM D5185m >15	0	0	---
Vanadium	ppm ASTM D5185m	<1	0	---
Cadmium	ppm ASTM D5185m	0	0	---

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	4	3	---
Barium	ppm ASTM D5185m 0	0	0	---
Molybdenum	ppm ASTM D5185m 60	59	60	---
Manganese	ppm ASTM D5185m 0	<1	<1	---
Magnesium	ppm ASTM D5185m 1010	938	889	---
Calcium	ppm ASTM D5185m 1070	1055	1075	---
Phosphorus	ppm ASTM D5185m 1150	898	1012	---
Zinc	ppm ASTM D5185m 1270	1237	1215	---
Sulfur	ppm ASTM D5185m 2060	2874	3207	---

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	6	3	---
Sodium	ppm ASTM D5185m	5	0	---
Potassium	ppm ASTM D5185m >20	2	1	---

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	1.6	0.3	---
Nitration	Abs/cm *ASTM D7624 >20	11.8	6.2	---
Sulfation	Abs/.1mm *ASTM D7415 >30	24.6	18.4	---

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	21.5	14.2	---
Base Number (BN)	mg KOH/g ASTM D2896 9.8	5.1	9.2	---







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.1	14.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0103597 **Received** : 19 Dec 2023
Lab Number : 06039958 **Diagnosed** : 20 Dec 2023
Unique Number : 10795187 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 958 - Tri County HC Morton
 1090 W. Jefferson St.
 Morton, IL
 US 61550
 Contact: Bryan Link
 blink@gflenv.com
 T:
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)