

# **OIL ANALYSIS REPORT**

### Sample Rating Trend



NORMAL



Machine Id

# **International 4415**

Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- GAL)

# DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil


## **Fluid Condition**


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

JAL)		May2019	Jan2020 Mar2020	Feb2021 May2021 Jul2022	Dec2023	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0071447	PCA0045405	PCA0013104
Sample Date		Client Info		07 Dec 2023	24 Jul 2022	11 May 2021
Machine Age	mls	Client Info		119170	95325	95325
Oil Age	mls	Client Info		23845	9214	3322
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>130	54	36	16
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	14	10	5
Lead	ppm	ASTM D5185m	>20	0	0	<1
Copper	ppm	ASTM D5185m	>125	10	6	6
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Antimony	ppm	ASTM D5185m				0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	<1	3	16
Barium	ppm	ASTM D5185m	0	0	2	0
Molybdenum	ppm	ASTM D5185m	50	64	60	61
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	950	932	873	957
Calcium	ppm	ASTM D5185m	1050	1036	1039	1118
Phosphorus	ppm	ASTM D5185m	995	804	924	1041
Zinc	ppm	ASTM D5185m	1180	1207	1192	1203
Sulfur	ppm	ASTM D5185m	2600	2371	3044	2701
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	4	3
Sodium	ppm	ASTM D5185m		0	<1	1
Potassium	ppm	ASTM D5185m	>20	13	14	4
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>6	0.9	0.6	0.2
Nitration	Abs/cm	*ASTM D7624	>20	13.2	12.2	7.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.0	22.0	19.1
FLUID DEGRA	OATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	23.2	19.4	15.1
Base Number (BN)	mg KOH/g	ASTM D2896		5.5	7.4	8.9
, ,	,					



# **OIL ANALYSIS REPORT**








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.5	11.0	11.4

# **GRAPHS**











Laboratory Sample No. Lab Number Unique Number : 10795495

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 06040266

: PCA0071447

Recieved Diagnosed

: 20 Dec 2023 : 21 Dec 2023 Diagnostician : Sean Felton

Test Package : FLEET ( Additional Tests: FT-IR(Diff) ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

ICSB370 - Alton 4525 North Alby Road

Godfrey, IL US 62035 Contact: Chad Ingold c.ingold@illinois-central.com

T: (618)466-5400