

OIL ANALYSIS REPORT

Sample Rating Trend





Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

AL)	-) New1022 Fed022 Med023 Meg1023 Seg1023 Ged023 Ged023 Ged023 Ged023 Ged023							
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		GFL0101099	GFL0098465	GFL0098480		
Sample Date		Client Info		05 Dec 2023	31 Oct 2023	17 Oct 2023		
Machine Age	hrs	Client Info		0	0	150		
Oil Age	hrs	Client Info		0	600	600		
Oil Changed		Client Info		Not Changd	Changed	Not Changd		
Sample Status				NORMAL	NORMAL	NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2		
Fuel		WC Method	>5	<1.0	<1.0	<1.0		
Water		WC Method	>0.2	NEG	NEG	NEG		
Glycol		WC Method		NEG	NEG	NEG		
WEAR METAL	S	method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>110	7	10	8		
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1		
Nickel	ppm	ASTM D5185m	>2	0	0	<1		
Titanium	ppm	ASTM D5185m		0	0	<1		
Silver	ppm	ASTM D5185m	>2	0	0	0		
Aluminum	ppm	ASTM D5185m	>25	3	2	2		
Lead	ppm	ASTM D5185m	>45	0	<1	<1		
Copper	ppm	ASTM D5185m	>85	<1	0	<1		
Tin	ppm	ASTM D5185m	>4	<1	<1	1		
Vanadium	ppm	ASTM D5185m		<1	0	0		
Cadmium	ppm	ASTM D5185m		<1	0	<1		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m	0	37	4	<1		
Barium	ppm	ASTM D5185m	0	0	0	0		
Molybdenum	ppm	ASTM D5185m	60	65	57	50		
Manganese	ppm	ASTM D5185m	0	0	<1	<1		
Magnesium	ppm	ASTM D5185m	1010	382	888	887		
Calcium	ppm	ASTM D5185m	1070	1766	1144	1060		
Phosphorus	ppm	ASTM D5185m	1150	1100	1019	903		
Zinc	ppm	ASTM D5185m	1270	1298	1224	1190		
Sulfur	ppm	ASTM D5185m	2060	3597	3033	2906		
CONTAMINAN	ITS	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>30	4	4	4		
Sodium	ppm	ASTM D5185m		4	3	3		
Potassium	ppm	ASTM D5185m	>20	3	2	4		
INFRA-RED		method	limit/base	current	history1	history2		
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.2		
Nitration	Abs/cm	*ASTM D7624	>20	9.0	7.2	5.8		
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.6	19.5	17.8		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2		
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.0	15.4	13.5		
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.4	8.0	7.8		
					0.0			




12

Й

Ab

Nov16/22 Feb.6/23


OIL ANALYSIS REPORT



Aav74/73

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	13.7	13.8
GRAPHS						

3RAPH Ferrous Alloys



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)