


OIL ANALYSIS REPORT

(16068Z) Walgreens - Tractor [Walgreens - Tractor] 136A61359

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Feb.2023 Multi23 Deciti23						
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0111108	PCA0101920	PCA0092808
Sample Date		Client Info		04 Dec 2023	28 Jul 2023	16 Feb 2023
Machine Age	mls	Client Info		444039	396060	344733
Oil Age	mls	Client Info		50000	50000	50000
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	24	27	26
Chromium	ppm	ASTM D5185m	>5	2	2	2
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>30	12	14	15
Lead	ppm	ASTM D5185m	>30	0	<1	<1
Copper	ppm	ASTM D5185m	>150	4	6	5
Tin	ppm	ASTM D5185m	>5	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	1	2
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	62	66	62
Manganese	ppm	ASTM D5185m	0	<1	<1	1
Magnesium	ppm	ASTM D5185m	950	978	1015	893
Calcium	ppm	ASTM D5185m	1050	1117	1225	1151
Phosphorus	ppm	ASTM D5185m	995	1078	1044	874
Zinc	ppm	ASTM D5185m	1180	1311	1336	1172
Sulfur	ppm	ASTM D5185m	2600	2861	3324	2616
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	4	5	5
Sodium	ppm	ASTM D5185m		2	3	2
Potassium	ppm	ASTM D5185m	>20	5	6	7
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1.3	1.4	1.4
Nitration	Abs/cm	*ASTM D7624	>20	10.3	10.6	10.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.5	23.6	24.5
FLUID DEGRA	NOITAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.5	19.2	19.3
Base Number (BN)	mg KOH/g	ASTM D2896		4.9	5.0	4.9




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method	ilmit/base		nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	12.00	11.7	11.5	11.4

GRAPHS











Certificate L2367

Laboratory Sample No.

Lab Number Unique Number : 10802458 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0111108 : 06041850

Recieved : 21 Dec 2023 Diagnosed Diagnostician : Wes Davis

: 22 Dec 2023

Transervice - Shop 1370 - Berkeley-Perrysburg

28727 Oregon Road Perrysburg, OH US 43551

Contact: Curtis Hart chart@transervice.com

T: (419)666-3277 F: (419)666-3279

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)