

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
Plymouth & Brockton
 Machine Id
11450
 Component
Transmission (Auto)
 Fluid
EXTENDED LIFE COOLANT (26 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.

Fluid Condition

Confirm oil type. The AN level is acceptable for this fluid. The condition of the fluid is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0104486	---	---
Sample Date	Client Info		05 Dec 2023	---	---
Machine Age	mls	Client Info	77039	---	---
Oil Age	mls	Client Info	77039	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			NORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.1	NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>230	137	---
Chromium	ppm	ASTM D5185m	>2	<1	---
Nickel	ppm	ASTM D5185m	>5	2	---
Titanium	ppm	ASTM D5185m	>2	<1	---
Silver	ppm	ASTM D5185m	>5	0	---
Aluminum	ppm	ASTM D5185m	>65	33	---
Lead	ppm	ASTM D5185m	>55	50	---
Copper	ppm	ASTM D5185m	>85	13	---
Tin	ppm	ASTM D5185m	>5	5	---
Vanadium	ppm	ASTM D5185m		0	---
Cadmium	ppm	ASTM D5185m		0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		124	---
Barium	ppm	ASTM D5185m		0	---
Molybdenum	ppm	ASTM D5185m		2	---
Manganese	ppm	ASTM D5185m		2	---
Magnesium	ppm	ASTM D5185m		<1	---
Calcium	ppm	ASTM D5185m		44	---
Phosphorus	ppm	ASTM D5185m		353	---
Zinc	ppm	ASTM D5185m		0	---
Sulfur	ppm	ASTM D5185m		988	---


CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	7	---
Sodium	ppm	ASTM D5185m		7	---
Potassium	ppm	ASTM D5185m	>20	6	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.92	---

OIL ANALYSIS REPORT




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.1	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	37.3	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0104486 **Recieved** : 21 Dec 2023
Lab Number : 06042270 **Diagnosed** : 23 Dec 2023
Unique Number : 10802878 **Diagnostician** : Don Baldrige
Test Package : MOB 2

PLYMOUTH & BROCKTON
 8 INDUSTRIAL PARK RD
 PLYMOUTH, MA
 US 02360
 Contact: Donald Pelpquin
 Dpelquin@P-B.com
 T: (508)732-6039
 F: (508)732-6091

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)