

OIL ANALYSIS REPORT

Sample Rating Trend





Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


| AL) | | Au | 2021 | Jan2023 Dec20 | 3 | |
|------------------|----------------|----------------------------|--------------|---------------|---------------|--------------|
| SAMPLE INFOR | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | PCA0112278 | PCA0073230 | PCA0054772 |
| Sample Date | | Client Info | | 14 Dec 2023 | 14 Jan 2023 | 13 Aug 2021 |
| Aachine Age | mls | Client Info | | 223446 | 166295 | 80994 |
| Dil Age | mls | Client Info | | 223446 | 0 | 12000 |
| Dil Changed | | Client Info | | Changed | Changed | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINAT | ION | method | limit/base | current | history1 | history2 |
| uel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Vater | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METAL | .S | method | limit/base | current | history1 | history2 |
| ron | ppm | ASTM D5185m | >100 | 17 | 14 | 10 |
| Chromium | ppm | ASTM D5185m | >20 | 0 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >4 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | 2 | 3 | <1 |
| Silver | ppm | ASTM D5185m | >3 | 0 | <1 | <1 |
| Aluminum | ppm | ASTM D5185m | >20 | 7 | 5 | 7 |
| ead | ppm | ASTM D5185m | >40 | 0 | <1 | <1 |
| Copper | ppm | ASTM D5185m | >330 | 2 | 1 | 2 |
| īn | ppm | ASTM D5185m | >15 | 0 | <1 | <1 |
| Antimony | ppm | ASTM D5185m | | | | 0 |
| /anadium | ppm | ASTM D5185m | | <1 | <1 | <1 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 2 | 2 | 8 | 16 |
| Barium | ppm | ASTM D5185m | 0 | 0 | 1 | 0 |
| /lolybdenum | ppm | ASTM D5185m | 50 | 54 | 58 | 51 |
| Manganese | ppm | ASTM D5185m | 0 | <1 | <1 | <1 |
| Magnesium | ppm | ASTM D5185m | 950 | 914 | 731 | 724 |
| | ppm | ASTM D5185m | 1050 | 1125 | 1153 | 1377 |
| Phosphorus | ppm | ASTM D5185m | 995 | 1031 | 951 | 971 |
| Zinc Sulfur | ppm ppm | ASTM D5185m ASTM D5185m | 1180 2600 | 1258 2898 | 1120 2725 | 1194 2725 |
| CONTAMINAN | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 6 | 6 | 5 |
| Sodium | ppm | ASTM D5185m | ~ | 3 | 1 | 2 |
| Potassium | ppm | ASTM D5185m | >20 | 9 | 10 | 22 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.6 | 0.4 | 0.3 |
| Vitration | Abs/cm | *ASTM D7624 | >20 | 9.0 | 9.0 | 8.8 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 21.1 | 20.0 | 20.1 |
| FLUID DEGRA | DAT <u>ION</u> | method | limit/base | current | history1 | history2 |
| Dxidation | Abs/.1mm | *ASTM D7414 | >25 | 16.9 | 15.8 | 15.1 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | | 6.8 | 7.5 | |
| 52:07) Rev: 1 | 0 - 0 | | | | on: ROSTY VIT | |


Contact/Location: ROSTY VITER - MILPHINE



OIL ANALYSIS REPORT







Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Ň

Laboratory

Sample No.

F: (215)552-9892