




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
732M
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0105871	GFL0069853	---
Sample Date	Client Info		20 Dec 2023	07 Jun 2023	---
Machine Age	hrs	Client Info	19877	19833	---
Oil Age	hrs	Client Info	19833	600	---
Oil Changed	Client Info		Not Changed	Changed	---
Sample Status			NORMAL	SEVERE	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.2	NEG	NEG	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >80	0	36	---
Chromium	ppm	ASTM D5185m >5	0	1	---
Nickel	ppm	ASTM D5185m >2	0	<1	---
Titanium	ppm	ASTM D5185m	0	0	---
Silver	ppm	ASTM D5185m >3	0	0	---
Aluminum	ppm	ASTM D5185m >30	<1	3	---
Lead	ppm	ASTM D5185m >30	0	<1	---
Copper	ppm	ASTM D5185m >150	<1	<1	---
Tin	ppm	ASTM D5185m >5	0	<1	---
Vanadium	ppm	ASTM D5185m	0	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	4	5	---
Barium	ppm	ASTM D5185m 0	0	0	---
Molybdenum	ppm	ASTM D5185m 60	59	49	---
Manganese	ppm	ASTM D5185m 0	<1	<1	---
Magnesium	ppm	ASTM D5185m 1010	943	807	---
Calcium	ppm	ASTM D5185m 1070	1011	891	---
Phosphorus	ppm	ASTM D5185m 1150	1132	902	---
Zinc	ppm	ASTM D5185m 1270	1267	1078	---
Sulfur	ppm	ASTM D5185m 2060	3218	2347	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >20	5	6	---
Sodium	ppm	ASTM D5185m	2	6	---
Potassium	ppm	ASTM D5185m >20	<1	1	---
Fuel	%	ASTM D3524 >5	0.3	13.6	---

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0	0.9	---
Nitration	Abs/cm	*ASTM D7624 >20	4.2	12.2	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	17.2	23.0	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	12.8	21.0	---
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	9.0	5.8	---







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.8	10.6

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0105871 Recieved : 22 Dec 2023
 Lab Number : 06043866 Diagnosed : 27 Dec 2023
 Unique Number : 10804474 Diagnostician : Wes Davis
 Test Package : FLEET (Additional Tests: PercentFuel)

GFL Environmental - 415 - Michigan East
 6200 Elmridge
 Sterling Heights, MI
 US 48313
 Contact: Frank Wolak
 fwolak@gflenv.com
 T: (586)825-9514
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)