

OIL ANALYSIS REPORT

Sample Rating Trend





4643M Component

Machine Id

Diesel Engine Fluid

PETRO CANADA DURON

		DN SHP 15W40 (GAL)							
SAMPLE INFORM	/ ATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		GFL0107084	GFL0107016	GFL0096560			
Sample Date		Client Info		20 Dec 2023	11 Dec 2023	05 Dec 2023			
Machine Age	hrs	Client Info		16052	15972	15953			
Oil Age	hrs	Client Info		600	600	600			
Oil Changed		Client Info		Not Changd	N/A	Changed			
Sample Status				NORMAL	NORMAL	NORMAL			
CONTAMINATI	ON	method	limit/base	current	history1	history2			
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0			
Water		WC Method	>0.2	NEG	NEG	NEG			
Glycol		WC Method		NEG	NEG	NEG			
WEAR METALS	S	method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>90	9	42	26			
Chromium	ppm	ASTM D5185m	>20	<1	1	<1			
Nickel	ppm	ASTM D5185m	>2	0	0	0			
Titanium	ppm	ASTM D5185m	>2	0	0	0			
Silver	ppm	ASTM D5185m	>2	0	0	0			
Aluminum	ppm	ASTM D5185m	>20	2	6	2			
Lead	ppm	ASTM D5185m	>40	0	<1	0			
Copper	ppm	ASTM D5185m	>330	<1	2	<1			
Tin	ppm	ASTM D5185m	>15	0	0	0			
Vanadium	ppm	ASTM D5185m		0	0	0			
Cadmium	ppm	ASTM D5185m		0	0	0			
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m	0	0	<1	0			
Barium	ppm	ASTM D5185m	0	0	0	0			
Molybdenum	ppm	ASTM D5185m	60	60	61	56			
Manganese	ppm	ASTM D5185m	0	0	0	0			
Magnesium	ppm	ASTM D5185m	1010	924	1096	892			
Calcium	ppm	ASTM D5185m	1070	1072	1243	1032			
Phosphorus	ppm	ASTM D5185m	1150	934	1131	850			
Zinc	ppm	ASTM D5185m	1270	1223	1336	1183			
Sulfur	ppm	ASTM D5185m	2060	2947	2807	3009			
CONTAMINAN	TS	method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>25	2	11	8			
Sodium	ppm	ASTM D5185m		2	7	5			
Potassium	ppm	ASTM D5185m	>20	2	3	0			
INFRA-RED		method	limit/base	current	history1	history2			
Soot %	%	*ASTM D7844	>6	0.3	1.3	0.4			
Nitration	Abs/cm	*ASTM D7624	>20	8.5	12.7	9.2			
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.5	25.6	20.0			
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2			
	AL / 4	*ASTM D7414	>25	15.0	22.7	17.2			
Oxidation	Abs/.1mm	ASTIVI D7414	>20	15.0	<u> </u>	17.2			

DIAGNOSIS Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination


There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.




OIL ANALYSIS REPORT





15 10

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.5	14.9	13.0
GRAPHS						
Ferrous Alloys						
iron A						
chromium			1			
15 nickel		NI				
	Λ		112			
	1	\ /	1			



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Ĕ