


Area  
**Process Cheese [98666552]**  
 Machine Id  
**BLENDER 6**  
 Component  
**Gearbox**  
 Fluid  
**GEAR OIL ISO 320 (--- GAL)**



## DIAGNOSIS

- Recommendation**  
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.
- Wear**  
All component wear rates are normal.
- Contamination**  
There is a high amount of particulates present in the oil.
- Fluid Condition**  
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>PCA0114269</b>	PCA0088324	PCA0073984
Sample Date	Client Info	<b>17 Dec 2023</b>	14 May 2023	03 Dec 2022
Machine Age	hrs	<b>0</b>	0	0
Oil Age	hrs	<b>0</b>	0	0
Oil Changed	Client Info	<b>Changed</b>	Changed	Changed
Sample Status		<b>ABNORMAL</b>	ABNORMAL	ABNORMAL

## CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.2	<b>NEG</b>	NEG	NEG

## WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >200	<b>25</b>	14	4
Chromium	ppm ASTM D5185m >15	<b>&lt;1</b>	0	0
Nickel	ppm ASTM D5185m >15	<b>0</b>	0	0
Titanium	ppm ASTM D5185m	<b>&lt;1</b>	0	0
Silver	ppm ASTM D5185m	<b>0</b>	0	0
Aluminum	ppm ASTM D5185m >25	<b>4</b>	3	<1
Lead	ppm ASTM D5185m >100	<b>0</b>	0	0
Copper	ppm ASTM D5185m >200	<b>&lt;1</b>	<1	0
Tin	ppm ASTM D5185m >25	<b>0</b>	0	0
Vanadium	ppm ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 50	<b>0</b>	0	0
Barium	ppm ASTM D5185m 15	<b>0</b>	0	0
Molybdenum	ppm ASTM D5185m 15	<b>0</b>	0	0
Manganese	ppm ASTM D5185m	<b>0</b>	<1	0
Magnesium	ppm ASTM D5185m 50	<b>&lt;1</b>	<1	0
Calcium	ppm ASTM D5185m 50	<b>3</b>	<1	0
Phosphorus	ppm ASTM D5185m 350	<b>651</b>	632	631
Zinc	ppm ASTM D5185m 100	<b>66</b>	27	18
Sulfur	ppm ASTM D5185m 12500	<b>1477</b>	1448	771

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >50	<b>6</b>	3	4
Sodium	ppm ASTM D5185m	<b>&lt;1</b>	<1	0
Potassium	ppm ASTM D5185m >20	<b>1</b>	<1	0





## FLUID CLEANLINESS

method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >1300	<b>▲ 133430</b>	▲ 103428	▲ 119814
Particles >6µm	ASTM D7647 >320	<b>▲ 49885</b>	▲ 21430	▲ 30017
Particles >14µm	ASTM D7647 >80	<b>▲ 2260</b>	▲ 431	▲ 584
Particles >21µm	ASTM D7647 >20	<b>▲ 284</b>	▲ 61	▲ 91
Particles >38µm	ASTM D7647 >4	<b>2</b>	0	2
Particles >71µm	ASTM D7647 >3	<b>0</b>	0	0
Oil Cleanliness	ISO 4406 (c) >17/15/13	<b>▲ 24/23/18</b>	▲ 24/22/16	▲ 24/22/16

## FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN) mg KOH/g	ASTM D8045 0.85	<b>0.72</b>	0.60	0.52


# OIL ANALYSIS REPORT








PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

PARAMETER	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	323	319

### SAMPLE IMAGES



### GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0114269 **Received** : 27 Dec 2023  
**Lab Number** : 06046614 **Diagnosed** : 29 Dec 2023  
**Unique Number** : 10807222 **Diagnostician** : Doug Bogart  
**Test Package** : IND 2 ( Additional Tests: PrtCount )

**KraftHeinz - Springfield - Plant 8311 PCA**  
 2035 E BENNETT  
 SPRINGFIELD, MO  
 US 65804  
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: