


# OIL ANALYSIS REPORT

## Sample Rating Trend



**NORMAL**



Area  
**(AY878H) Supermarket - Tractor**  
Machine Id  
**FREIGHTLINER 107A3669**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 10W30 (11 GAL)**

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

### SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>PCA0110978</b>	PCA0104108	PCA0097071
Sample Date	Client Info		<b>22 Dec 2023</b>	29 Aug 2023	24 May 2023
Machine Age	mls	Client Info	<b>385178</b>	370405	351340
Oil Age	mls	Client Info	<b>14773</b>	19065	20494
Oil Changed	Client Info		<b>Changed</b>	Changed	Not Changed
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

### CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method		<b>NEG</b>	NEG	NEG

### WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >80	<b>16</b>	37	30
Chromium	ppm	ASTM D5185m >5	<b>&lt;1</b>	2	1
Nickel	ppm	ASTM D5185m >2	<b>0</b>	<1	<1
Titanium	ppm	ASTM D5185m	<b>0</b>	0	0
Silver	ppm	ASTM D5185m >3	<b>0</b>	<1	<1
Aluminum	ppm	ASTM D5185m >30	<b>7</b>	12	8
Lead	ppm	ASTM D5185m >30	<b>0</b>	0	1
Copper	ppm	ASTM D5185m >150	<b>4</b>	17	9
Tin	ppm	ASTM D5185m >5	<b>&lt;1</b>	<1	<1
Vanadium	ppm	ASTM D5185m	<b>0</b>	0	<1
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

### ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	<b>20</b>	17	46
Barium	ppm	ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m 50	<b>71</b>	74	78
Manganese	ppm	ASTM D5185m 0	<b>0</b>	2	<1
Magnesium	ppm	ASTM D5185m 950	<b>878</b>	892	859
Calcium	ppm	ASTM D5185m 1050	<b>1210</b>	1255	1183
Phosphorus	ppm	ASTM D5185m 995	<b>1018</b>	981	984
Zinc	ppm	ASTM D5185m 1180	<b>1185</b>	1288	1222
Sulfur	ppm	ASTM D5185m 2600	<b>2948</b>	3140	3548

### CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >20	<b>4</b>	8	7
Sodium	ppm	ASTM D5185m	<b>&lt;1</b>	1	2
Potassium	ppm	ASTM D5185m >20	<b>2</b>	9	3



### INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	<b>0.8</b>	1.4	0.7
Nitration	Abs/cm	*ASTM D7624 >20	<b>7.5</b>	9.4	8.1
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>19.5</b>	22.9	20.6

### FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>14.5</b>	17.2	15.5
Base Number (BN)	mg KOH/g	ASTM D2896	<b>8.3</b>	6.4	8.0





# OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

PARAMETER	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.9	12.2

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0110978 **Received** : 28 Dec 2023  
**Lab Number** : 06046766 **Diagnosed** : 28 Dec 2023  
**Unique Number** : 10807374 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**Transervice - Shop 1071 - Supermarket-Dayton**  
 60 A Tower Road  
 Dayton, NJ  
 US 08810  
 Contact: Brian Quinn  
 bquinn@transervice.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: