

OIL ANALYSIS REPORT

CONTAMINATION

Sample Rating Trend

NORMAL

TOTAL A

LEGACY [98620005]


KR-GR-006003 - HYDRAULIC A/B (S/N OLD POWER HOUSE)

Component

Hydraulic System

PETRO CANADA PURITY FG HYDRAULIC AW 68 (30 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: 98620005)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0114827	PCA0100854	PCA0101933
Sample Date		Client Info		20 Dec 2023	22 Sep 2023	06 Jul 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	N/A	N/A
Sample Status				NORMAL	ABNORMAL	NORMAL

Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0	<1	<1
Chromium	ppm	ASTM D5185m	>20	0	0	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	0	0	<1
Lead	ppm	ASTM D5185m	>20	0	0	0
Copper	ppm	ASTM D5185m	>20	1	1	<1
Tin	ppm	ASTM D5185m	>20	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2


ADDITIVES		memou		HISTORY	HISTORYZ
Boron	ppm	ASTM D5185m	0	0	0
Barium	ppm	ASTM D5185m	0	2	0
Molybdenum	ppm	ASTM D5185m	0	0	0
Manganese	ppm	ASTM D5185m	0	0	<1
Magnesium	ppm	ASTM D5185m	0	<1	0
Calcium	ppm	ASTM D5185m	0	<1	0
Phosphorus	ppm	ASTM D5185m	377	371	400
Zinc	ppm	ASTM D5185m	<1	10	0
Sulfur	ppm	ASTM D5185m	383	367	454

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	13	▲ 15	7
Sodium	ppm	ASTM D5185m		1	0	0
Potassium	ppm	ASTM D5185m	>20	2	0	0

i otassiam	ррпп	NOTHI DOTOGIII	720	_	0	O .
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG



OIL ANALYSIS REPORT





GRAPHS Ferrous Alloys 10 Non-ferrous Metals Viscosity @ 40°C 240 220 200 180 (-) 160 (-) 140 (-) 140 र्छ ₁₂₀ 100 60 40



Certificate L2367

Laboratory Sample No. Lab Number Test Package : IND 1

: PCA0114827 : 06048101 Unique Number : 10808709

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 29 Dec 2023 : 02 Jan 2024 Diagnosed Diagnostician : Don Baldridge

KraftHeinz - Kirksville - Plant 8333 PCA 2504 INDUSTRIAL DR

KIRKSVILLE, MO US 63501

F: (660)627-5887

Contact: WALLACE WARD

wallace.ward@kraftheinzcompany.com T: (660)627-1031

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)