

OIL ANALYSIS REPORT

Sample Rating Trend









KEMP QUARRIES / KEMP STONE - FAIRLAND [67743] **WL128**

Component Front Right Final Driv

PETRO CANADA PRODU

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: PM-4 changed fluid)

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The condition of the oil is acceptable for the time in service.

re						
JRO TO-4 SAE 50 (- GAL)	Mar2019 Jan2020	Jul2020 Jan2021	Mar2022 Aug2022 Feb2023 Jul2	023 Dec202:	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0086568	PCA0084723	PCA0084603
Sample Date		Client Info		21 Dec 2023	06 Oct 2023	10 Jul 2023
Machine Age	hrs	Client Info		34924	34458	33887
Oil Age	hrs	Client Info		34924	34458	33887
Oil Changed		Client Info		Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	30	25	21
Chromium	ppm	ASTM D5185m	>10	0	3	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m	>15	<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	2	3	2
Lead	ppm	ASTM D5185m	>10	<1	0	0
Copper	ppm	ASTM D5185m	>75	1	<1	<1
Tin	ppm	ASTM D5185m	>8	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2


ADDITIVES		memou			HISTOLAL	HISTORYZ
Boron	ppm	ASTM D5185m	2	<1	0	5
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	<1	<1
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	9	17	15	14
Calcium	ppm	ASTM D5185m	3114	3216	3362	3380
Phosphorus	ppm	ASTM D5185m	1099	947	944	948
Zinc	ppm	ASTM D5185m	1245	1180	1210	1165
Sulfur	ppm	ASTM D5185m	7086	4719	4926	5735

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	33	35	34
Sodium	ppm	ASTM D5185m		1	0	0
Potassium	ppm	ASTM D5185m	>20	0	1	1


Potassium	ppm	ASTM D5185m	>20	0	1	1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG



OIL ANALYSIS REPORT









Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : MOB 1

: 06049659

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0086568 : 10810267

Recieved : 02 Jan 2024 : 04 Jan 2024 Diagnosed : Sean Felton Diagnostician

Kemp Quarries - Kemp Stone - Fairland

18350 S 590 Rd Fairland, OK US 74343

Contact:

F:

fairland@kempstone.com

T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)