




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
720014-361495
 Component
Diesel Engine
 Fluid
MFA 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0046118	GFL0046096	GFL0046116
Sample Date	Client Info	21 Dec 2023	10 Dec 2023	26 Oct 2023
Machine Age	hrs	450	450	0
Oil Age	hrs	450	0	0
Oil Changed	Client Info	Changed	Not Changd	Changed
Sample Status		NORMAL	NORMAL	ABNORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >3.0	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >120	4	20	▲ 126
Chromium	ppm ASTM D5185m >20	<1	<1	2
Nickel	ppm ASTM D5185m >5	<1	2	6
Titanium	ppm ASTM D5185m >2	0	0	<1
Silver	ppm ASTM D5185m >2	<1	0	0
Aluminum	ppm ASTM D5185m >20	2	4	▲ 23
Lead	ppm ASTM D5185m >40	<1	<1	6
Copper	ppm ASTM D5185m >330	<1	1	6
Tin	ppm ASTM D5185m >15	<1	0	2
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m	3	3	5
Barium	ppm ASTM D5185m	0	0	0
Molybdenum	ppm ASTM D5185m	59	59	62
Manganese	ppm ASTM D5185m	<1	<1	2
Magnesium	ppm ASTM D5185m	878	902	841
Calcium	ppm ASTM D5185m	1014	1066	1106
Phosphorus	ppm ASTM D5185m	1003	1007	973
Zinc	ppm ASTM D5185m	1239	1206	1216
Sulfur	ppm ASTM D5185m	2821	3044	2627

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	3	20	14
Sodium	ppm ASTM D5185m	5	4	10
Potassium	ppm ASTM D5185m >20	2	0	2

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >4	0.2	0.7	2.7
Nitration	Abs/cm *ASTM D7624 >20	9.0	8.9	17.2
Sulfation	Abs/.1mm *ASTM D7415 >30	20.5	20.4	32.3

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	16.2	17.1	30.6
Base Number (BN)	mg KOH/g ASTM D2896	5.4	8.9	6.3







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	13.4	13.4	13.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0046118 **Received** : 03 Jan 2024
Lab Number : **06049767** **Diagnosed** : 04 Jan 2024
Unique Number : 10815716 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 834 - Chillicothe Hauling
 201 Mitchell Road
 Chillicothe, MO
 US 64601
 Contact: Terry McKiddy
 tmckiddy@gflenv.com
 T: (816)225-6699
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)