




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
828056-101263

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0102275	GFL0060278	GFL0060292
Sample Date	Client Info		20 Dec 2023	20 Jan 2023	06 Oct 2022
Machine Age	hrs	Client Info	15739	13674	13048
Oil Age	hrs	Client Info	600	600	580
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	43	42	102
Chromium	ppm	ASTM D5185m >20	3	2	4
Nickel	ppm	ASTM D5185m >4	<1	<1	1
Titanium	ppm	ASTM D5185m	<1	<1	<1
Silver	ppm	ASTM D5185m >3	0	0	0
Aluminum	ppm	ASTM D5185m >20	9	5	15
Lead	ppm	ASTM D5185m >40	0	0	1
Copper	ppm	ASTM D5185m >330	2	2	2
Tin	ppm	ASTM D5185m >15	<1	<1	<1
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	7	3	1
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	55	63	60
Manganese	ppm	ASTM D5185m 0	<1	<1	1
Magnesium	ppm	ASTM D5185m 1010	875	924	928
Calcium	ppm	ASTM D5185m 1070	968	1040	1064
Phosphorus	ppm	ASTM D5185m 1150	951	942	945
Zinc	ppm	ASTM D5185m 1270	1165	1164	1315
Sulfur	ppm	ASTM D5185m 2060	2746	3232	3084

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	14	13	14
Sodium	ppm	ASTM D5185m	24	67	59
Potassium	ppm	ASTM D5185m >20	1	<1	2

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	1	1.1	1.6
Nitration	Abs/cm	*ASTM D7624 >20	10.7	11.9	19.2
Sulfation	Abs/.1mm	*ASTM D7415 >30	22.0	22.5	32.7

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	19.8	20.3	40.0
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	6.5	7.9	7.6







OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.1	13.6	15.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0102275 **Received** : 04 Jan 2024
Lab Number : **06051360** **Diagnosed** : 05 Jan 2024
Unique Number : 10817309 **Diagnostician** : Don Baldrige
Test Package : FLEET

GFL Environmental - 859 - Bay City
 700 Avenue F
 Bay City, TX
 US 77414
 Contact: TERESA DIXON
 teresa.dixon@gflenv.com
 T:
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)