


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id 2869 Component

Transmission (Auto)

PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The condition of the oil is acceptable for the time in service.

668 (GAL)		lep2022 Jan2	023 Mar2023 May2023	Jun2023 Jul2023 Sep2023 Oct	2023 Dec202:	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0107258	GFL0097932	GFL0097866
Sample Date		Client Info		29 Dec 2023	15 Nov 2023	12 Oct 2023
Machine Age	hrs	Client Info		2868	2607	2469
Oil Age	hrs	Client Info		641	380	242
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>160	17	40	41
Chromium	ppm	ASTM D5185m	>5	0	0	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m		6	12	12
Lead	ppm	ASTM D5185m		4	7	10
Copper	ppm	ASTM D5185m		3	4	6
Tin	ppm	ASTM D5185m		<1	0	2
Vanadium	ppm	ASTM D5185m	>10	0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	ррпп	method	limit/base		history1	history2
			IIIIII/Dase		· ·	•
Boron	ppm	ASTM D5185m		68	73	73 0
Barium	ppm	ASTM D5185m		0	0	
Molybdenum	ppm	ASTM D5185m		0	8	<1
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		<1	122	2
Calcium	ppm	ASTM D5185m		361	250	123
Phosphorus	ppm	ASTM D5185m		417	341	215
Zinc	ppm	ASTM D5185m		0	176	0
Sulfur	ppm	ASTM D5185m		1467	1527	1550
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	11	4	4
Sodium	ppm	ASTM D5185m		6	3	0
Potassium	ppm	ASTM D5185m	>20	1	0	2
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG





OIL ANALYSIS REPORT




	FLUID PROPE	RTIES	method	limit/base	current	history1	history2
٧	/isc @ 40°C	cSt	ASTM D445	34	32.3	38.1	33.7
	SAMPLE IMAG	ES	method	limit/base	current	history1	history2
C	Color				no image	no image	no image
E	Bottom				no image	no image	no image

GRAPHS











Laboratory Sample No. Lab Number Unique Number : 10819204 Test Package : FLEET

: 06053255

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0107258 Recieved : 05 Jan 2024 Diagnosed : 08 Jan 2024

Diagnostician : Don Baldridge

GFL Environmental - 010 - Stockbridge 1280 Rum Creek Parkway Stockbridge, GA

US 30281 Contact: JOSHUA TINKER

joshuatinker@gflenv.com T:

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)