


# **OIL ANALYSIS REPORT**

Sample Rating Trend



NORMAL



Machine Id **3768C** Component

**Natural Gas Engine** 

PETRO CANADA DURON GEO LD 15W40 (40 QTS)

# DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the

## **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


(40 QTS)	0 QTS)						
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		GFL0090080	GFL0070783	GFL0058583	
Sample Date		Client Info		20 Dec 2023	07 Apr 2023	09 Oct 2022	
Machine Age	hrs	Client Info		13580	12080	11430	
Oil Age	hrs	Client Info		600	600	0	
Oil Changed		Client Info		Changed	Changed	N/A	
Sample Status				NORMAL	NORMAL	NORMAL	
CONTAMINATION	ON	method	limit/base	current	history1	history2	
Water		WC Method	>0.1	NEG	NEG	NEG	
WEAR METALS	3	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>50	39	12	18	
Chromium	ppm	ASTM D5185m	>4	2	<1	1	
Nickel	ppm	ASTM D5185m	>2	<1	0	0	
Titanium	ppm	ASTM D5185m		0	0	0	
Silver	ppm	ASTM D5185m	>3	0	0	0	
Aluminum	ppm	ASTM D5185m	>9	5	2	4	
Lead	ppm	ASTM D5185m	>30	<1	0	0	
Copper	ppm	ASTM D5185m	>35	<1	0	<1	
Tin	ppm	ASTM D5185m	>4	<1	0	0	
Vanadium	ppm	ASTM D5185m		0	0	0	
Cadmium	ppm	ASTM D5185m		0	0	0	
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	50	54	17	11	
Barium	ppm	ASTM D5185m	5	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	52	45	48	
Manganese	ppm	ASTM D5185m	0	<1	<1	<1	
Magnesium	ppm	ASTM D5185m	560	604	509	506	
Calcium	ppm	ASTM D5185m	1510	1576	1413	1553	
Phosphorus	ppm	ASTM D5185m	780	953	633	646	
Zinc	ppm	ASTM D5185m	870	950	788	903	
Sulfur	ppm	ASTM D5185m	2040	2575	1985	2658	
CONTAMINANT	ΓS	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>+100	27	4	2	
Sodium	ppm	ASTM D5185m		4	5	8	
Potassium	ppm	ASTM D5185m	>20	7	0	<1	
INFRA-RED		method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844		0.4	0.1	0.1	
Nitration	Abs/cm	*ASTM D7624	>20	7.9	9.6	11.3	
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.6	19.6	22.7	
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.0	17.0	18.9	
		ACTM DOOGS		0.7	6.0	6.0	


9.7

Base Number (BN) mg KOH/g ASTM D2896 10.2



# **OIL ANALYSIS REPORT**








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.1	13.1	15.0	15.0

## **GRAPHS**













Certificate L2367

Laboratory Sample No. Lab Number Test Package : FLEET

**Unique Number** 

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0090080 : 06053611 : 10819560

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Recieved : 08 Jan 2024 Diagnosed : 09 Jan 2024 Diagnostician : Wes Davis

GFL Environmental - 030 - Conway Myrtle Beach

3010 HWY 378 Conway, SC US 29527

Contact: ARCILIO RUEZ

aruiz@gflenv.com T:

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: