

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id 929084-260355

Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| 6AL) | | | | | | |
|---|----------|-------------|------------|-------------|-------------|-------------|
| SAMPLE INFOR | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | GFL0102435 | GFL0102551 | GFL0098581 |
| Sample Date | | Client Info | | 19 Dec 2023 | 29 Nov 2023 | 08 Nov 2023 |
| Machine Age | hrs | Client Info | | 24524 | 23484 | 2425 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINAT | ION | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METAL | .S | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 11 | 7 | 17 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >4 | <1 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 2 | 2 | 1 |
| Lead | ppm | ASTM D5185m | >40 | 2 | <1 | 6 |
| Copper | ppm | ASTM D5185m | >330 | <1 | <1 | 4 |
| Tin | ppm | ASTM D5185m | >15 | <1 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 0 | 4 | 1 | 1 |
| Barium | ppm | ASTM D5185m | 0 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 60 | 62 | 58 | 63 |
| Manganese | ppm | ASTM D5185m | 0 | <1 | 0 | 0 |
| Magnesium | ppm | ASTM D5185m | 1010 | 1023 | 921 | 928 |
| Calcium | ppm | ASTM D5185m | 1070 | 1128 | 1012 | 1084 |
| Phosphorus | ppm | ASTM D5185m | 1150 | 1162 | 1026 | 983 |
| Zinc | ppm | ASTM D5185m | 1270 | 1404 | 1213 | 1204 |
| Sulfur | ppm | ASTM D5185m | 2060 | 3364 | 3066 | 2865 |
| CONTAMINAN | ITS | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 4 | 4 | 4 |
| Sodium | ppm | ASTM D5185m | | 4 | 3 | <1 |
| Potassium | ppm | ASTM D5185m | >20 | <1 | 2 | 2 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.5 | 0.3 | 0.5 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 6.8 | 6.0 | 9.0 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 20.3 | 18.9 | 21.9 |
| FLUID DEGRADATION method limit/base current history1 history2 | | | | | | |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 15.4 | 14.5 | 18.4 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 9.8 | 8.3 | 8.6 | 7.8 |
| , , | | | | | | |



OIL ANALYSIS REPORT








| VISUAL | | method | limit/base | current | history1 | history2 |
|-------------------------|--------|---------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |


| FLUID PROPE | RHES | metnoa | ilmit/base | current | nistory i | nistory2 |
|--------------|------|-----------|------------|---------|-----------|----------|
| Visc @ 100°C | cSt | ASTM D445 | 15.4 | 13.8 | 14.1 | 14.1 |

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : FLEET

: 10820587

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0102435 : 06054638

Recieved : 08 Jan 2024 : 09 Jan 2024 Diagnosed Diagnostician : Wes Davis

GFL Environmental - 837 - Harrison TS

22820 S State Route 291 Harrisonville, MO US 64701

Contact: BRYAN SWANSON bryanswanson@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: