




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Machine Id  
**12035**

Component  
**Diesel Engine**

Fluid  
**PETRO CANADA DURON SHP 15W40 (11 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>GFL0089647</b>	GFL0089655	GFL0089584
Sample Date	Client Info	<b>02 Jan 2024</b>	15 Dec 2023	17 Nov 2023
Machine Age	hrs	<b>0</b>	0	0
Oil Age	hrs	<b>0</b>	0	0
Oil Changed	Client Info	<b>Not Changed</b>	Not Changed	Not Changed
Sample Status		<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method >0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method	<b>NEG</b>	NEG	NEG

## WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >110	<b>5</b>	8	19
Chromium	ppm ASTM D5185m >4	<b>&lt;1</b>	<1	<1
Nickel	ppm ASTM D5185m >2	<b>&lt;1</b>	0	0
Titanium	ppm ASTM D5185m	<b>0</b>	0	<1
Silver	ppm ASTM D5185m >2	<b>0</b>	0	0
Aluminum	ppm ASTM D5185m >25	<b>1</b>	1	2
Lead	ppm ASTM D5185m >45	<b>0</b>	0	<1
Copper	ppm ASTM D5185m >85	<b>&lt;1</b>	<1	1
Tin	ppm ASTM D5185m >4	<b>&lt;1</b>	<1	0
Vanadium	ppm ASTM D5185m	<b>&lt;1</b>	<1	0
Cadmium	ppm ASTM D5185m	<b>0</b>	<1	0

## ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	<b>4</b>	3	2
Barium	ppm ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm ASTM D5185m 60	<b>58</b>	61	62
Manganese	ppm ASTM D5185m 0	<b>&lt;1</b>	0	<1
Magnesium	ppm ASTM D5185m 1010	<b>915</b>	930	914
Calcium	ppm ASTM D5185m 1070	<b>1010</b>	991	1039
Phosphorus	ppm ASTM D5185m 1150	<b>1009</b>	1034	954
Zinc	ppm ASTM D5185m 1270	<b>1206</b>	1248	1184
Sulfur	ppm ASTM D5185m 2060	<b>2921</b>	3125	2704

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >30	<b>4</b>	3	6
Sodium	ppm ASTM D5185m	<b>2</b>	4	7
Potassium	ppm ASTM D5185m >20	<b>3</b>	2	4

## INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	<b>0.1</b>	0.5	0.8
Nitration	Abs/cm *ASTM D7624 >20	<b>5.9</b>	7.2	9.8
Sulfation	Abs/.1mm *ASTM D7415 >30	<b>17.8</b>	18.5	20.6

## FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	<b>13.8</b>	14.0	16.8
Base Number (BN)	mg KOH/g ASTM D2896 9.8	<b>7.8</b>	8.1	6.8







# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.3</b>	13.5	13.5

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0089647 **Recieved** : 10 Jan 2024  
**Lab Number** : **06056550** **Diagnosed** : 11 Jan 2024  
**Unique Number** : 10822499 **Diagnostician** : Don Baldrige  
**Test Package** : FLEET

**GFL Environmental - 732 - Thomaston Hauling**  
 2616 Waynmanville Road  
 Thomaston, GA  
 US 30286  
 Contact: WILLIAM BROWN  
 william.brown@gflenv.com  
 T: (706)936-4065  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)