


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
48

Component
Natural Gas Engine

Fluid
PETRO CANADA SENTRON LD 3000 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

Tests indicate that there is no fuel present in the oil. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0111964	PCA0111952	PCA0103429
Sample Date	Client Info		02 Jan 2024	04 Dec 2023	01 Nov 2023
Machine Age	hrs	Client Info	96333	95638	94847
Oil Age	hrs	Client Info	3326	2631	1840
Oil Changed		Client Info	Not Chngd	Not Chngd	Not Chngd
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.1	NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	8	3	2
Chromium	ppm	ASTM D5185m >4	0	<1	0
Nickel	ppm	ASTM D5185m >2	0	0	0
Titanium	ppm	ASTM D5185m	0	0	0
Silver	ppm	ASTM D5185m >3	0	0	0
Aluminum	ppm	ASTM D5185m >9	2	<1	<1
Lead	ppm	ASTM D5185m >30	0	0	0
Copper	ppm	ASTM D5185m >35	1	0	0
Tin	ppm	ASTM D5185m >4	0	0	0
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 5	0	0	<1
Barium	ppm	ASTM D5185m 1	0	0	0
Molybdenum	ppm	ASTM D5185m 2	5	3	1
Manganese	ppm	ASTM D5185m 1	0	<1	<1
Magnesium	ppm	ASTM D5185m 5	10	12	11
Calcium	ppm	ASTM D5185m 1220	1328	1305	1294
Phosphorus	ppm	ASTM D5185m 298	323	287	288
Zinc	ppm	ASTM D5185m 350	331	353	343
Sulfur	ppm	ASTM D5185m 1995	2504	2375	2426

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >+100	4	4	4
Sodium	ppm	ASTM D5185m	1	5	4
Potassium	ppm	ASTM D5185m >20	35	32	18
Fuel	%	ASTM D3524 >4.0	0.0	0.0	0.0





INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0	0	0
Nitration	Abs/cm	*ASTM D7624 >20	6.2	5.3	4.4
Sulfation	Abs/.1mm	*ASTM D7415 >30	15.3	14.5	14.0

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	10.1	9.1	8.0
Acid Number (AN)	mg KOH/g	ASTM D8045 0.86	1.26	1.42	0.51
Base Number (BN)	mg KOH/g	ASTM D2896 3.85	2.31	4.14	3.69









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	13.7	13.4	13.2

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0111964 **Recieved** : 10 Jan 2024
Lab Number : 06057445 **Diagnosed** : 12 Jan 2024
Unique Number : 10823394 **Diagnostician** : Wes Davis
Test Package : MOB 2 (Additional Tests: FuelDilution, PercentFuel)

ENERVEST OPERATING - POPLAR GAP A
 1618 CRESCENT ROAD
 GRUNDY, VA
 US 24614
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: